

MasterProtect® 180

A non-toxic solvent free high build, protective epoxy resin coating

DESCRIPTION

MasterProtect 180 is a protective high build epoxy resin coating specifically developed to protect concrete and steel. Supplied as a two-pack system comprising pigmented base and a hardener, it requires only on site mixing to produce an easily applied decorative and chemically resistant finish. MasterProtect 180 can be safely used in areas where contact with foodstuffs is envisaged or for coating potable water storage tanks. It is solvent free and can be used with safety in small rooms or tanks without the need to provide special ventilation. MasterProtect 180 coatings will not support the growth of bacteria. MasterProtect 180 has been tested according to BS 6920 conformity test for use in water up to 50°C.

PRIMARY USES

For the internal protection of concrete or metal tanks containing drinking water, certain chemicals, oils and fuel. Contact your Master Builders Solutions representative for further advice. As an impervious, resilient and chemically resistant floor or wall coating in food manufacturing plants, breweries, canning and bottling factories. As a gas and vapor barrier.

As a protective and decorative coating in laboratories, abattoirs, etc. Other usage areas include oil refineries, paper mills, power stations, garages, hospitals, sugar refineries, hangars and most liquid containment areas.

APPEARANCE AND FINISH

High gloss, heavy bodied, ultra dense surface. Hygienic and easily cleaned. Standard colors are light grey and dusty grey.

ADVANTAGES

- Durable
- Non-toxic
- Waterproof and protective
- High chemical resistance
- High temperature water resistance
- Solvent free
- High build coating
- Easily applied by brush or roller

PACKAGING

MasterProtect 180 is supplied in 10 liter.

TYPICAL PROPERTIES

Working life at 30°C: 30 minutes
Mixed density at 25°C: 1.6g/cm³
Initial cure 12 hours@ 30°C

Final cure 4 days @ 30°C

Coverage: 0.29 - 0.40kg / m² /

coat

Finished film thickness: 180-240 microns

per coat

Bond to concrete: In excess of the

cohesive strength of

concrete

APPLICATION PROCEDURE SURFACE PREPARATION:

The substrate should be a smooth or semi-smooth sound surface such as concrete or metal. It is most important to ensure that thorough surface preparation is undertaken prior to application of the MasterProtect 180 coating.

CONCRETE

Ensure concrete is free from excessive laitance, grease, oil, curing compound, etc. Ensure concrete is sound, cutting back where necessary and making good using suitable Master Builders Solutions MasterEmaco or MasterBrace repair systems. Ensure all blow holes and surface imperfections are made good prior to application of the

MasterProtect 180 coating.

Ensure concrete is at least 28 days old. Contamination by oil, grease, fats etc. must be removed before other forms of preparation begin. Remove laitance to expose blow holes, by light grit blasting.

STEEL:

All previous surface treatments should be removed taking the surface back to base metal. The base metal should be abraded and preferably shot blasted with grit, steel shot or proprietary abrasive. Where shot blasting is



MasterProtect® 180

A non-toxic solvent free high build, protective epoxy resin coating

impractical pre-treatment may be carried out with pneumatic de-scaling guns, tap hammers, rotary wire brushes or by flame scaling. Cleaning with solvent or a strong detergent is advisable to ensure surface is free from grease etc. Do not allow surface to re-oxidise before application of **MasterProtect 180**.

MIXING:

MasterProtect 180 is supplied in two pre-weighed components, base and reactor. No additions or omissions are required. Add reactor contents to the base component and mix thoroughly for using a slow speed drill fitted with a suitable mixing paddle until a uniform streak free color is achieved.

APPLICATION:

MasterProtect 180 coating can be applied using good quality rollers or short haired brushes or by airless spray. It is recommended that MasterProtect 180 coating be applied in two coats of contrasting colors to ensure complete coverage.

Prior to the application of each coat the surface should be examined for signs of pin-holing, etc. Where pin-holing is evident these should be filled using **MasterBrace ADH 2200** thixotropic epoxy resin filler.

If the application is delayed more than 16 hours at 40°C or 36 hours at 20°C after the previous coat (the higher the ambient temperature, the shorter the maximum period), then the previous coat must be thoroughly abraded to give an adequate mechanical key and solvent wiped.

AIRLESS SPRAY

For application by airless spray, use a 45:1 or higher ratio pump, minimum 9mm dia. hoses and HD tip 19-23 thou.

OVERCOATING:

Where areas need to be overcoated due to damage etc. it is important that the areas to be treated are well abraded using a stiff rotary wire brush or coarse sand paper to give an adequate key. Completely strip off any unsound coating and proceed with overcoating as for new work.

CHEMICAL RESISTANCE

MasterProtect 180 is resistant to intermittent spillages of the following typically encountered chemicals:

- Formaldehyde, 40% solution
- Sulphuric Acid, 50% solution
- Hydrochloric Acid, 50% solution
- Hydrochloric Acid 5% solution
- Lactic Acid, 50% solution
- Nitric Acid, 10% solution
- Sodium Hydroxide, 50% solution
- Diesel oil
- Wine
- Sea and brackish water
- Aviation hydraulic fuels (Skydrol)
- Vegetable oils

Note: Higher concentration of mineral acids may cause matting of the surface and color changes.

EQUIPMENT CARE

All equipment must be cleaned immediately after use with MasterTop Thinner No. 2. Similar cleaning procedures should be adopted for break periods exceeding 15 minutes duration.

SPECIFICATION CLAUSE

MasterProtect 180: Where indicated, apply MasterProtect 180 protective epoxy coating as manufactured by Master Builders Solutions, or similar approved to the following specification:

Composition: Two component, non-toxic,

pigmented solvent less epoxy resin

based compound.

Coverage: 0.29 to 0.40kg/m²/coat, two coats are

recommended.

Dry film thickness 180 to 240 microns/coat.

STORAGE

Store under cover out of direct sunlight and protect from extremes of temperature. In tropical climates the product must be stored in an air conditioned environment. Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult Master Builders Solutions's Technical Services Department.



MasterProtect® 180

A non-toxic solvent free high build, protective epoxy resin coating

SAFETY PRECAUTIONS

As with all chemical products, care should be taken during use and storage to avoid contact with eyes mouth, skin and foodstuffs. Treat splashes to eyes and skin immediately. If accidentally ingested, seek immediate medical attention. Keep away from children and animals. Reseal containers after use. For further information, refer to material safety data sheet.

NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local Master Builders Solutions representative.

Master Builders Solutions reserves the right to have the true cause of any difficulty determined by accepted test methods.

QUALITY AND CARE

All Master Builders Solutions Products are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health and safety standards of ISO 9001 and Master Builders Solutions ESHQ recommendations.

* Properties listed are based on laboratory controlled tests

® = Registered trademark of the MBCC-Group in many countries

CONTACT

Should you require any further information, please do not hesitate to contact us:

www.master-builders-solutions.com/en-sa enquirycc.saudi@mbcc-group.com M: +966 13 853 8600

Master Builders Solutions Saudi Arabia for Manufacturing LLC. P.O. Box 1884, Al Khobar, KSA

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

Disclaimer:

In view of widely varying site conditions and fields of application of our products, this technical data sheet is meant to provide general application guidelines only. This information is based on our present knowledge and experience. The customer is not released from the obligation to conduct careful testing of suitability and possible application for the intended use. The customer is obliged to contact the technical help-line for fields of application not expressly stated in the technical data sheet under "Fields of Application". Use of the product beyond the fields of application as stated in the technical data sheet without previous consultation with Master Builders Solutions and possible resulting damages are in the sole responsibility of the customer.

All descriptions, drawings, photographs, data, ratios, weights i.e. stated herein can be changed without advance notice and do not represent the condition of the product as stipulated by contract. It is the sole responsibility of the recipient of our products to observe possible proprietary rights as well as existing laws and provisions. The reference of trade names of other companies is no recommendation and does not exclude the use of products of similar type. Our information only describes the quality of our products and services and is no warranty. Liability is accepted for incomplete or incorrect particulars in our data sheets only in the event of intent or gross negligence, without prejudice to claims under product liability laws.