

# MasterSeal<sup>®</sup> NP 2

Multiple-component high-performance polyurethane sealant

## DESCRIPTION

**MasterSeal NP 2** is a multi-component, highly flexible, non-priming, high performance polyurethane sealant. It has been successfully tested for joint movement of  $\pm 25\%$ . It can be tinted to multiple colors.

## FEATURES

- Joint movement capability  $\pm 25\%$  provides excellent flexibility for keeping moving joints weathertight
- Weather resistant for long-lasting weathertight seals
- Easy to gun and tool to speed up application and make neater joints
- No primer required for most construction materials, lowering installation costs
- Wide temperature application range makes **MasterSeal NP 2** suitable for all climates
- UL listed; Passes 4-hour, 4-inch, fire and hose stream test when used with Ultra Blockor mineral wool
- Suitable for water immersion with documented performance in wet areas
- Chemical cure allows for faster turnaround time
- Bulk packaging results in less waste
- Long pot life provides extended working time
- Formulated to withstand pedestrian and vehicular traffic

## APPLICATIONS

- Interior and exterior
- Above and below grade
- Immersed in water
- Expansion joints
- Panel walls
- Precast units
- Aluminum and wood window frames
- Roofing
- Fascia
- Parapets and vinyl siding
- Store front assemblies
- Parking structures

## PACKAGING

**MasterSeal NP 2** is available in 5.67 units.

Available in pre-tinted colors: Precast Gray and Limestone.

## COLORS

40 standard, stocked colors are available. Refer to Master Builders Solutions Color Portfolio for additional colors.

## STANDARDS

- ASTM C 920, Type M, Grade NS, Class 25, use NT, T, A, M, O\* and I
- Federal Specification TT-S-00227E, Type II, Class A
- Corps of Engineers CRD-C-506
- Canadian Standards Board CAN/CGSB-19.24-M90, Classification MCG-2-40-A-N, No. 81029
- CFI accepted
- USDA compliant for use in meat and poultry areas
- Underwriters Laboratories Inc.® classified (fire resistance only).

## SHELF LIFE

Shelf life is 1 year when stored in unopened containers under normal conditions.

## STORAGE

Store in unopened containers in a cool, clean, dry area. Do not open containers until ready for use.

## VOC CONTENT

When mixed, product contains less than 64.4 g/L less water and exempt solvents

# MasterSeal<sup>®</sup> NP 2

Multiple-component high-performance polyurethane sealant

## TEST PROPERTIES\*

PROPERTY	RESULTS	TEST METHOD
Movement Capability, %	±25	ASTM C 719
Tensile strength, MPa	1.1	ASTM D 412
Ultimate elongation at break, %	280	ASTM D 412
Stain and color change	Passes (no visible stain)	ASTM C 510
Extrusion rate, sec, 3 hrs after mixing	6, Passes	ASTM C 603
Rheological (flow), at 49°C	Non-sag	ASTM C 639
Hardness, Shore A		ASTM C 661
At standard conditions	25	
After heat aging (max Shore A:50)	22	
Tack-free time, hrs, (maximum 72 hrs)	< 48 hours	ASTM C 679
Bond durability*, %, on aluminium and concrete	Passes	ASTM C 719
Weight loss, after heat aging, %	4.7	ASTM C 792
Cracking and chalking, after heat aging	None	ASTM C 792
Artificial weathering, Xenon arc, 2,000 hours	No surface cracking	ASTM G 26
Adhesion in peel, on aluminium and concrete*, pli	> 10	ASTM C 794
Water immersion, 50° C	Passes 10 weeks with movement cycle	ASTM C 1247

\*Primed for water immersion dictated by ASTM C 920. Concrete and aluminum primed with **MasterSeal P 173**; glass primed with **MasterSeal P 176**

Test results are typical values obtained under laboratory conditions. Reasonable variations can be expected.

## TYPICAL PROPERTIES

Property	Value
Temperature range (°C)	-40 to 82
Shrinkage	None

### Joint Width and Sealant Depth

Joint Width, (mm)	Sealant depth at midpoint, (mm)
6-13	6
13-19	6-10
19-25	10-13
25-75	13

### Working time, hours

Standard Conditions, 23°C, 50% RH	Higher Temperature 35°C, 5-90% RH	Colder Temperature 4°C
2-3	1-2	4-6

### Yield, Meters per liter

		Joint width (mm)									
		6	10	13	16	19	22	25	38	50	75
Joint depth (mm)	6	24.8	16.5	12.4	9.8	-	-	-	-	-	-
	10	-	-	-	6.6	5.5	4.7	4.1	-	-	-
	13	-	-	-	-	4.1	3.5	3.0	2.2	1.5	0.7

# MasterSeal® NP 2

Multiple-component high-performance polyurethane sealant

## How to apply:

### JOINT PREPARATION

1. The product may be used in sealant joints designed in accordance with SWR Institute's Sealants - The Professional's Guide.
2. In optimal conditions, the depth of the sealant should be ½ the width of the joint. The sealant joint depth (measured at the center) should always fall between the maximum depth of 12mm and the minimum depth of 6mm. Maximum recommended joint width is 75mm. Refer to Table 1.
3. In deep joints, the sealant depth must be controlled by closed cell backer rod or soft backer rod. Where the joint depth does not permit the use of backer rod, a bond breaker (polyethylene strip) must be used to prevent three-point bonding.
4. To maintain the recommended sealant depth, install backer rod by compressing and rolling it into the joint channel without stretching it lengthwise. Closed cell backer rod should be about 3mm larger in diameter than the width of the joint to allow for compression. Soft backer rod should be approximately 25% larger in diameter than the joint width. The sealant does not adhere to it, and no separate bond breaker is required. Do not prime or puncture the backer rod.

### SURFACE PREPARATION

Substrates must be structurally sound, fully cured, dry and clean. Substrates should always be free of the following: dirt, loose particles, oil, grease, asphalt, tar, paint, wax, rust, waterproofing or curing and parting compounds, membrane materials and sealant residue.

### CONCRETE, STONE, AND OTHER MASONRY

Clean by grinding, sandblasting or wire brushing to expose a sound surface free of contamination and laitance.

### WOOD

New and weathered wood must be clean, dry and sound. Scrape away loose paint to bare wood. Any coatings on wood must be tested to verify adhesion of sealant or to determine an appropriate primer.

### METAL

Remove scale, rust and loose coatings from metal to expose a bright white surface. Any coatings on metal must be tested to verify adhesion of sealant or to determine an appropriate primer.

### PRIMING

1. **MasterSeal NP 2** is generally considered a non-priming sealant, but special circumstances or substrates (e.g., certain protective coatings on aluminium) may require a primer. It is the user's responsibility to check the adhesion of the cured sealant on typical test joints at the project site before and during application. Refer to Technical Data Guide on **MasterSeal P 173**, and consult Master Builders Solutions Technical Services for additional information.
2. Apply primer at full strength with a brush or clean cloth. A light, uniform coating is sufficient for most surfaces. Porous surfaces require more primer, however, do not over-apply.
3. Allow primer to dry before applying **MasterSeal NP 2**.
4. Depending on temperature and humidity, primer will be tack free in 15 to 120 minutes. Priming and sealing must be done on the same work day.

### MIXING

1. **MasterSeal NP 2** is a multi-component system with a configuration of Part A, Part B and a color pack.
2. Transfer entire contents of Part B to Part A container using a spatula or margin trowel.
3. Part B must be mixed thoroughly with Part A. Before adding pigment, scrape sides of container to ensure complete mixing of Parts A and B. With a slow-speed drill and a sealant mixing paddle, mix 4–6 minutes. Keep the paddle blade below the surface of the sealant to avoid whipping air into the sealant.
4. Transfer the entire contents of one **MasterSeal 900** pigment can into the mixed Part A and B. Use a spatula or knife to remove all the pigment from the container. Continue mixing with a slow-speed drill and slotted paddle until color is uniform. During the process, scrape the sides and bottom of the mixing container several times to obtain a complete mix.

# MasterSeal® NP 2

Multiple-component high-performance polyurethane sealant

## APPLICATION

Except when unusual job conditions dictate the use of knife or spatula, apply MasterSeal NP 2 by professional bulk gun loaded at the jobsite. Fill joints from the bottom up to the exterior face by holding a properly sized nozzle against the joint bottom.

Dry tooling is recommended. Proper tooling results in the correct bead shape, neat joints, and optimal adhesion.

Best practices dictate that all caulking and sealing be done when temperatures are above 40°F (4°C) to avoid application to moisture-laden surfaces. Moisture on substrates will adversely affect adhesion.

Application may proceed as low as 40°F (4°C) if there is certainty that substrates are completely dry, free of moisture and clean as described under Surface Preparation.

## CURING

The cure of **MasterSeal NP 2** varies with temperature and humidity. The following times assume 75°F (24°C), 50% relative humidity, and a joint 13mm in width by 6mm in depth.

- Skins: within 3–4 hours
- Full cure: approximately 1 week

See Table 2 for use of **MasterSeal 905** accelerator.

## CLEAN UP

Immediately after use and before sealant has cured, clean equipment with **MasterTop THN 2**. Cured sealant may be removed by cutting with a sharp-edged tool. Remove thin films by abrading.

## FOR BEST PERFORMANCE

- Pursuant to accepted industry standards and practices, using rigid paints and/or coatings over flexible sealants can result in a loss of adhesion of the applied paint and/or coating, due to the potential movement of the sealant. However, should painting and/or coating be desired, it is required that the applicator of the paint and/or coating conduct on-site testing to determine compatibility and adhesion.

- Do not allow uncured **MasterSeal NP 2** to come into contact with alcohol-based materials or solvents.
- Do not use as a cap, heel or toe bead for exterior glazing.
- Do not apply polyurethane sealants in the vicinity of uncured silicone sealants or uncured **MasterSeal NP 150**.
- **MasterSeal NP 2** should not come in contact with oil-based caulking, silicone sealants, polysulfides or fillers impregnated with oil, asphalt or tar.
- Do not apply epoxy-based coatings in the vicinity of uncured **MasterSeal NP 2**.
- Do not apply to freshly treated wood; treated wood must have weathered for at least 6 months.
- Do not open containers until ready for use.
- Units are premeasured; do not use partial units.
- **MasterSeal NP 2** may yellow in the presence of unvented artificial heat; this is a surface phenomenon that does not affect sealant performance.
- When **MasterSeal NP 2** is used in areas subject to continuous water immersion, cure for 14 days at 70°F (23°C). Allow longer cure times at lower temperatures. Always use Master Seal P 173.
- Do not use in swimming pools, or on other submerged conditions where the sealant will be exposed to strong oxidizers. Avoid submerged conditions where water temperatures will exceed 120°F (50°C).
- Horizontal joints subject to traffic or intermittent ponding of water require the use of primer. Call Technical Service for details.
- Substrates such as copper, stainless and galvanized steel typically require the use of a primer; **MasterSeal P 173** or **MasterSeal P 176** are acceptable. For Kynar coatings, use **MasterSeal P 173** only. An adhesion test is recommended for any other questionable substrate.
- Use only **MasterSeal 900** color packs designed for use with **MasterSeal NP 2**.
- Proper application is the responsibility of the user. Field visits by Master Builders Solutions personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.

# MasterSeal<sup>®</sup> NP 2

Multiple-component high-performance polyurethane sealant

## RISKS

May cause skin, eye or respiratory irritation. May cause dermatitis and allergic responses. Potential skin and/or respiratory sensitizer. Ingestion may cause irritation. Reports associate repeated or prolonged occupational overexposure to solvents with permanent brain, nervous system, liver and kidney damage. **INTENTIONAL MISUSE BY DELIBERATELY INHALING THE CONTENTS MAY BE HARMFUL OR FATAL.**

## PRECAUTIONS

**KEEP OUT OF THE REACH OF CHILDREN.** Use only with adequate ventilation Prevent contact with skin, eyes, and clothing. Wash thoroughly after handling. Use impervious gloves, eye protection and if the TLV is exceeded or used in a poorly ventilated area, use NIOSH / MSHA approved respiratory protection in accordance with applicable federal, state, and local regulations.

## FIRST AID

In case of eye contact, flush thoroughly with water at least 15 minutes. **SEEK IMMEDIATE MEDICAL ATTENTION.** In case of skin contact, wash affected areas with soap and water. If irritation persists, seek medical attention. Remove and wash contaminated clothing If inhalation effects occur, remove to fresh air. If discomfort persists or any breathing difficulty occurs, or if swallowed, **SEEK IMMEDIATE MEDICAL ATTENTION.** Refer to Material Safety Data Sheet (MSDS) for further information.

## NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local Master Builders Solutions representative.

Master Builders Solutions reserves the right to have the true cause of any difficulty determined by accepted test methods.

## QUALITY AND CARE

All Master Builders Solutions Products are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health and safety standards of ISO 9001 and Master Builders Solutions ESHQ recommendations.

\* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the MBCC-Group in many countries

## CONTACT

Should you require any further information, please do not hesitate to contact us:

[www.master-builders-solutions.com/en-sa](http://www.master-builders-solutions.com/en-sa)  
[enquirycc.saudi@mbcc-group.com](mailto:enquirycc.saudi@mbcc-group.com)  
M: +966 13 853 8600

Master Builders Solutions Saudi Arabia for Manufacturing LLC.  
P.O. Box 1884, Al Khobar, KSA

## STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

### Disclaimer:

In view of widely varying site conditions and fields of application of our products, this technical data sheet is meant to provide general application guidelines only. This information is based on our present knowledge and experience. The customer is not released from the obligation to conduct careful testing of suitability and possible application for the intended use. The customer is obliged to contact the technical help-line for fields of application not expressly stated in the technical data sheet under "Fields of Application". Use of the product beyond the fields of application as stated in the technical data sheet without previous consultation with Master Builders Solutions and possible resulting damages are in the sole responsibility of the customer.

All descriptions, drawings, photographs, data, ratios, weights i.e. stated herein can be changed without advance notice and do not represent the condition of the product as stipulated by contract. It is the sole responsibility of the recipient of our products to observe possible proprietary rights as well as existing laws and provisions. The reference of trade names of other companies is no recommendation and does not exclude the use of products of similar type. Our information only describes the quality of our products and services and is no warranty. Liability is accepted for incomplete or incorrect particulars in our data sheets only in the event of intent or gross negligence, without prejudice to claims under product liability laws.