

MasterTile® 30

Cementitious, polymer modified tile adhesive for non-vitrified, vitrified, glass mosaic, porcelain and non-moisture sensitive natural stones tiles

DESCRIPTION

MasterTile 30 is a cement based tile adhesive for thin or thick bed fixing of ceramic tiles in interior or exterior situations, especially those exposed to permanently wet conditions.

Suitable substrates are concrete, sand cement screeds and renders, plaster boards, gypsum fibre boards and suitably prepared timber.

TYPICAL APPLICATIONS

MasterTile 30 is the adhesive of choice for swimming pools and may be used with confidence in all wet process applications including: abattoirs, shower rooms, institutional kitchens, bathrooms, and decorative, high risk cladding. **MasterTile 30** may be used to tile directly onto glazed tile surfaces and is especially recommended for non-porous or high density and glass mosaics where it may be used to both fix and grout.

Used in conjunction with **MasterTile RSG 705**, the system is suitable for use where chemical resistance or a high standard of hygienic quality is essential.

For extreme conditions such as vibration or temperature extremes etc. **MasterTile 30** can be mixed with **MasterTile A 200** instead of water.

MasterTile 30 mixed with **MasterTile A 200** is suitable for fixing certain types of natural stone. Please consult Master Builders Solutions Technical Service Department for advice.

MasterTile 30 is a blend of Portland cement, and graded sand, reinforced with a high organic polymer content

ADVANTAGES

- Waterproof: immersion will not affect adhesion.
- Non-slip.
- Ready for use - just add water.
- Thin or thick bed.
- Exceeds British Standard requirements.
- Extended open / wet time.
- High adhesive bond strength.

PACKAGING

MasterTile 30 is available in 20kg bags.

COMPOSITION

MasterTile 30 is a blend of Portland cement, and graded sand, reinforced with a high organic polymer content.

TYPICAL PROPERTIES

Colors:	Off white and Grey
Plastic density	1800 kg/m ³
Yield	A 20 kg bag mixed with 3.6-4.0 L of water yields approximately 13.1-13.3 L of mixed adhesive
Curing times** (on slightly absorbent substrates)	
Walked on after	approx. 24 h
Groutable after	approx. 24 h
Able to bear weight after	approx. 7 days
** At +23°C and 50% relative humidity. Higher temperatures reduce, lower temperatures increase the times given.	

STANDARDS

BS 5980 Part 10 : 1980 ANSI A 118.1 ANSI A 118.4 (**MasterTile 30** mixed with **MasterTile A 200**)

COVERAGE

Solid bed fixing	:	3 - 6 mm depth 5.4 kg - 10.8 kg/m ²
Notched trowel application on to a smooth surface (trowel @ 45°)		
10 mm Notch		6.3 kg/m ² (3.17 m ² /bag)
8 mm Notch		5.4 kg/m ² (3.7 m ² /bag)
6 mm Notch		3.6 kg/m ² (5.55 m ² /bag)
4 mm Notch		2.7 kg/m ² (7.4 m ² /bag)

MasterTile[®] 30

Cementitious, polymer modified tile adhesive for non-vitrified, vitrified, glass mosaic, porcelain and non-moisture sensitive natural stones tiles

Above figures are to be used as a guide only and do NOT take into account surface undulation or material wastage.

APPLICATION GUIDELINES

Surfaces to be tiled, should be sound, dimensionally stable, clean and free from loose laitance, paint, oil, grease, mould release agent and residual curing compound. It should be ensured that tiles are dry, and free of contaminants that could impair adhesion.

SURFACE PREPARATION

Porous concrete, mortars, renders, plaster boards and gypsum fibre boards should be primed with **MasterTile P 302** to reduce suction.

Timber surfaces should be checked to ensure rigidity and soundness to accept the additional loading without deflection.

Provision must be made to ensure adequate ventilation beneath tiled timber flooring. Tongue and groove, parquet and sprung floorings must first be strengthened by screwing 12mm thick exterior grade plywood at 200mm centres onto the existing timber base.

Timber partition walls should be stiffened by screwing at 200mm centres onto studding, in both directions.

Timber surfaces should always be primed with **MasterCast 141 / CEMENT SLURRY**. **MasterCast 141 / CEMENT SLURRY** should only be applied after **MasterTile 30** has been mixed, to ensure adhesive is ready to apply immediately onto wet primer.

MIXING INSTRUCTIONS

Add **MasterTile 30** to cool, clean water at the following rates:

Place approx. 4 L gauging water in a clean mixing vessel. Mix to a uniform lump free consistency and allow to stand for 5 min. before use. Full bag volumes should be mixed in a forced action mixer.

Part bags should preferably be mixed using a slow speed drill and mixing paddle.

APPLICATION INSTRUCTIONS

Apply **MasterTile 30** to a uniform thickness of 3mm 6mm or sufficient to cover the studs or keys on the tile back; (on a working area of not more than 1m²). Solid bed fixing is recommended for wet conditions and for ceramic and marble flooring tiles, and vertical heavy duty applications including decorative stone cladding. If preferred, the **MasterTile 30** can additionally be buttered on the backs of the tiles to ensure full adhesive contact.

For all other vertical application the adhesive bed should be combed horizontally with a notched trowel to remove excess.

Tiles should be dry and fixed by pressing into place with slight twisting motion, ensuring the tile back achieves full contact with the adhesive.

Ceramic tiles should never be butt joined. Leave a minimum of 2mm around tiles. Adjustments to tiles should only be made during the adhesives open wet time.

Remove excess adhesive from the face of the tile with a damp sponge or cloth before it sets. Similarly, joints must be raked out in readiness for grouting.

Leave for a minimum of 24 hours before grouting. Select the appropriate grout for joint size and in service use from the **MasterTile** range of products.

WATCHPOINTS

Movement joints should be provided in accordance with normal practice. Refer to published local standards or BS 5385.

MasterTile 30 should not be used on painted or metal surfaces. The use of chilled mixing water will extend open wet time in high ambient temperatures.

Gypsum plaster boards and surfaces, must be subjected to pre-treatment. Please consult Master Builders Solutions's Technical Services Department for advice.

MasterTile[®] 30

Cementitious, polymer modified tile adhesive for non-vitrified, vitrified, glass mosaic, porcelain and non-moisture sensitive natural stones tiles

STORAGE AND SHELF LIFE

Store out of direct sunlight, clear of the ground on pallets protected from rainfall. Avoid excessive compaction. The shelf life is 12 months when stored as above.

SAFETY PRECAUTIONS

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs. Treat splashes to eyes and skin immediately. If accidentally ingested, seek immediate medical attention. Reseal containers after use. For further information, refer to material safety data sheet.

NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local Master Builders Solutions representative. Master Builders Solutions reserves the right to have the true cause of any difficulty determined by accepted test methods.

QUALITY AND CARE

All Master Builders Solutions Products are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health and safety standards of ISO 9001 and Master Builders Solutions ESHQ recommendations.

*Properties listed are based on laboratory controlled tests.

® = Registered trademark of the MBCC Group in many countries.

CONTACT

Should you require any further information, please do not hesitate to contact us:

www.master-builders-solutions.com/en-sa
enquirycc.saudi@mbcc-group.com
M: +966 13 853 8600

Master Builders Solutions Saudi Arabia for Manufacturing LLC.
P.O. Box 1884, Al Khobar, KSA

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

Disclaimer:

In view of widely varying site conditions and fields of application of our products, this technical data sheet is meant to provide general application guidelines only. This information is based on our present knowledge and experience. The customer is not released from the obligation to conduct careful testing of suitability and possible application for the intended use. The customer is obliged to contact the technical help-line for fields of application not expressly stated in the technical data sheet under "Fields of Application". Use of the product beyond the fields of application as stated in the technical data sheet without previous consultation with Master Builders Solutions and possible resulting damages are in the sole responsibility of the customer.

All descriptions, drawings, photographs, data, ratios, weights i.e. stated herein can be changed without advance notice and do not represent the condition of the product as stipulated by contract. It is the sole responsibility of the recipient of our products to observe possible proprietary rights as well as existing laws and provisions. The reference of trade names of other companies is no recommendation and does not exclude the use of products of similar type. Our information only describes the quality of our products and services and is no warranty. Liability is accepted for incomplete or incorrect particulars in our data sheets only in the event of intent or gross negligence, without prejudice to claims under product liability laws.