

# MasterRoc<sup>®</sup> SA 545 (Formerly known as Meyco<sup>®</sup> SA 545)

## Alkali-Free, Non-Caustic and Non-Toxic High Performance Powder Accelerator for Dry-Mix Sprayed Concrete

### DESCRIPTION OF PRODUCT

**MasterRoc<sup>®</sup> SA 545** is a high performance alkalifree, non caustic and non toxic accelerator for use in the dry-mix sprayed concrete process. It is a powder additive whose dosage can be varied to the desired setting and hardening times.

### FIELDS OF APPLICATION

**MasterRoc<sup>®</sup> SA 545** is suitable for all applications where high early strength, high final strength and very thick sprayed concrete layers are required.

- For temporary and permanent ground support in tunnelling and mining
- Slope stabilization
- For repair works

### FEATURES AND BENEFITS

- Overhead layer thickness of 10-15 cm in a single application
- Rapid work process
- Good early strength development
- Limits the decrease of final strength
- Improves durability as compared to mixes with traditional accelerators
- Provides an improved working environment
- Reduces salt content in leaching water

### APPLICATION PROCEDURE

The substrate must be clean and free from loose particles and preferably damp. It is recommended to only use fresh cement as the age of the cement can have a negative influence on the setting characteristics of the mix.

**MasterRoc<sup>®</sup> SA 545** is sensitive to the type of cement. With some cements the obtained setting characteristics can be too slow. This sensitivity can be compensated by reducing the water content. We recommend the use of Portland cements (PC/HPC), which normally give faster setting than blended or sulphate resistant cement types. In any case, it is strongly recommended to carry out preliminary tests to check the setting and the 24 hour strength characteristics of the cements planned for use in a project.

### TECHNICAL DATA

Form	Powder
Color	White
Bulk Density	1030 -1100 kg/m <sup>3</sup>
Ph value (En Iso 787-9)	4±1
Chloride Content	<0.1%

Evaluation of setting and 24 hour strength characteristics:

Initial set	Final set	24 h strength	Rating
2 min.	6-8 min.	18-20 MPa	good
5 min.	8-12 min.	12-15 MPa	OK
>10min.	>15 min.	<10 MPa	poor

### Concrete Mix

The minimum cement content with the use of **MasterRoc<sup>®</sup> SA 545** is 350 kg per m<sup>3</sup>. It is normally added to the mix immediately prior to use.

A combination of **MasterRoc<sup>®</sup> SA 545** and **MasterRoc<sup>®</sup> HCA 10** hydration control admixture prolongs the open time of the mix.

- Dosage: 0.4% by weight of binder of **MasterRoc<sup>®</sup> HCA 10** at ambient temperatures of >+20°C.
- At ambient temperatures between +15°C and +20°C only 0.2% by weight of binder should be used.
- Below +15°C **MasterRoc<sup>®</sup> HCA 10** should not be used at all.

### PACKAGING

**MasterRoc<sup>®</sup> SA 545** is supplied in 20 kg bags.

### CONSUMPTION

The consumption of **MasterRoc<sup>®</sup> SA 545** also depends on the water added, temperature conditions (dry mix and ambient), cement reactivity and on required layer thickness, setting time and early strength development. The consumption is normally in the range of 4 to 8% of binder weight.

Overdosing (>10%) may result in decreased final strength.

### STORAGE

If stored dry and in tightly closed original bags, **MasterRoc<sup>®</sup> SA 545** has a shelf life of 12 months. If subjected to humidity, the product loses its effectiveness. Any lumps can simply be crushed by hand. Material which is too hard must be discarded.

## MasterRoc® SA 545 (Formerly known as Meyco® SA 545)

**Alkali-Free, Non-Caustic and Non-Toxic High Performance Powder Accelerator for Dry-Mix Sprayed Concrete**

### SAFETY PRECAUTIONS

The same precautions as with handling and use of cementitious products should be observed. Avoid eye and skin contact and wear rubber gloves and safety glasses. If contact occurs, rinse with plenty of water. In case of eye contact seek medical advice. For further information, refer to the Material Safety Data Sheet or contact your local **Master Builders Solutions** representative.

### DISCLAIMER

The technical information given in this publication is based on the present state of our best scientific and practical knowledge. **Master Builders Solutions Yapı Kimyasalları Sanayi ve Ticaret Ltd. Şti.** is only responsible for the quality of the product **Master Builders Solutions Yapı Kimyasalları Sanayi ve Ticaret Ltd. Şti.** is not responsible for results that may occur because the product is used other than advised and/or out of instructions regarding the place and the method of use. This technical form is valid only till a new version is implemented and nullifies the old ones.

### CONTACT INFORMATION

**Master Builders Solutions Yapı Kimyasalları Sanayi ve Ticaret Ltd. Şti.**

Adres: Barbaros Mah. Begonya Sok.

Nidakule Kuzey Ataşehir, C Kapısı

No:3 E/5, 34746 Ataşehir İstanbul / Türkiye


Tel: 0216 217 88 00

Mail: [mbs.tr@mbcc-group.com](mailto:mbs.tr@mbcc-group.com)

Web: [www.master-builders-solutions.com/tr-tr](http://www.master-builders-solutions.com/tr-tr)

® Registered trademark of a MBCC Group member in many countries of the world

**MasterRoc® SA 545** Technical Data Sheet -Revision  
Date: 12/2020

 1020	
Master Builders Solutions Yapı Kimyasalları Sanayi ve Ticaret Ltd. Şti. Adres: Barbaros Mah. Begonya Sok. Nidakule Kuzey Ataşehir, C Kapısı No:3 E/5, 34746 Ataşehir İstanbul 20 Dop No: TR16/02/01 1020 - CPR - 040 065836 EN 934-5:2007 MasterRoc SA 545 Püskürtme Beton için Toz Priz Hızlandırıcı; EN 934 - 5 : T2 (Set Accelerator for Sprayed Concrete ; EN 934 - 5 : T2)	
Klorür İçeriği (Chloride Content)	<% 0,1 Kütlece (in mass)
Alkali İçeriği (Alkali Content)	<% 1 Kütlece (in mass)
Korozyona Etkisi (Corrosion Behaviour)	Yok (None)
Tehlikeli Maddeler (Dangerous Substances)	Yok (None) (1999/CE , 2001/60 /CE)