

MasterTile® JF 565

Cement Based Grouting with High Resistance Especially Designed for Swimming Pools

DESCRIPTION OF PRODUCT

MasterTile® JF 565 is a cement based, easily applied grouting material used in places like pools, baths, saunas, spas for the grouting of overlays like pool ceramics, granite ceramics, marble, glass, mosaic, porcelain ceramics.

Complies with EN 13888 - CG2WA class

CG2= Enhanced Cement based grouting (fulfilling additional properties)


W= Reduced Water absorption property

A= Highly abrasion-resistant

FIELDS OF APPLICATION

- In indoor and outdoor spaces, in vertical and horizontal applications,
- In the grouting of pool ceramics, granite ceramics, marble, glass mosaics, porcelain ceramics adhered to existent surfaces,
- In swimming pools and decoration pools,
- In water reservoirs,
- In baths and saunas,
- In terraces and balconies,
- In areas where mechanical and chemical cleaning is performed.

TECHNICAL DATA

Structure Of The Material	It Contains High Technology Filling, Sythetic Additives and Special Cement.	
Pressure Resistance	≥50 N/mm ²	
Bending Resistance	≥2,50 N/mm ²	
Contraction Value	≤3 mm/m	
Abrasion Resistance	≤1000 mm ³	
Water Absorbtion: 30 minutes 240 minutes	≤2 gr ≤5 gr	
Application Surface Temperature	+5°C +30°C	
Service Temperature	-20°C +250°C	
Maturation Period	3-5 minutes	
Usage Duration	60 minutes	
Regimentation Duration: Walking Over Duration Exposure To Water	6 hours 24 hours	

All figures are at +23°C with a relative humidity of 50%. High temperatures cause shorter cure times and vice versa.

FEATURES AND BENEFITS

- It attains an excellent resistance to pool and cleaning chemicals with its high technology.
- It reduces dirt penetration to a minimum with its high density structure.
- It is resistant to neutral and alkali cleaning substances.
- When compared with other cement based interliners its endurance against acidic cleaners has been increased.
- It can endure +250°C and being cleaned with a water jet with a high pressure of 100 bars.
- It is suitable for grouting hole widths from 1 mm up to 8 mm.
- It solidifies without cracks.
- It is freeze-thaw cycle resistant.
- It has one part. It is easily applied and cleaned like other cement based interliners.

APPLICATION PROCEDURE

Preparation of Substrate

Before filling the pool ceramic, granite ceramic, marble, glass mosaic, porcelain ceramic grouting holes it must be waited for the used adhesive to achieve sufficient hardness. Just before pplying MasterTile® JF 565, the surface must be cleaned with mechanical methods without being harmed and must be dampened with a wet sponge.

Mixing

Pour the amount of water indicated in the Mixing Ratios table into a clean mixing container with the assistance of a measuring cup. Add MasterTile® JF 565 slowly while mixing with a mixer that has a revolving frequency of 400-600 rev/min for about 3 - 5 minutes until a homogeneous

MasterTile® JF 565

Cement Based Grouting with High Resistance Especially Designed for Swimming Pools

mixture without pellets is obtained. Set it aside for about 3-5 minutes and the material becomes ready to use after it is mixed again for 30 more seconds.

Mixing Ratio

MasterTile® JF 565	For 1 kg of Powder	For 20 kg Bag
Mixture Water	Max. 0,20 liter	Max. 4,00 liter
Mixture Density	~2,22 kg/liter	

APPLICATION METHOD

Spread **MasterTile® JF 565** over the ceramics with a rubber trowel and fill the grouting interspaces. Skim the excessive material off the grouting holes diagonally. In deep grouting holes, first wait for the settling of the material and then repeat this procedure. Wait until the material can withstand the pressure of a finger and upon cleaning the whole surface with a wet sponge, give the life water that is necessary for the completion of the hydration. Clean the remaining materials on the surface of the ceramics with a wet sponge and give the final shape to the interlines. After the material gets dry (the day after by the latest), polish up the ceramics with a dry and clean oakum.

COVERAGE

Ceramic Dimensions	MasterTile® JF 565					
	Coverage Table For Cement Based Grouting, Grouting Hole Depth, 8 mm					
	Grouting Widths					
	2 mm (gr/m ²)	3 mm (gr/m ²)	4 mm (gr/m ²)	5 mm (gr/m ²)	6 mm (gr/m ²)	8 mm (gr/m ²)
2,5X2,5	2500	3700	-	-	-	-
5X5	-	1900	-	-	-	-
10X10	-	1000	1350	1750	2100	2800
10X20	-	750	1050	1300	1550	2050
20X20	-	550	750	900	-	-
30X30	-	350	500	600	-	-

WATCH POINTS

- **MasterTile® JF 565** must be mixed with the assistance of mechanical mixers, it definitely must not be mixed with a trowel.
- Avoid **MasterTile® JF 565** application under excessive heat or wind and/or when the ambient and/or substrate temperature is below +5 or above +30.
- Do not add water and new material to a **MasterTile® JF 565** mixture which has started getting dry under any circumstances. Ceramics with high water absorbing capacity must be saturated with water before the application.
- About 10 - 20 minutes after the application of the material a test must be made by exerting pressure with a finger.
- If no material is getting smudged on the fingers in the finger test, the process of giving life water to the interlines must be started. Thus dust extraction of the interlines, or their getting cracked is prevented and a perfect surface regularity is achieved.

- The surface cleansing procedure must not be carried out by using sawdust.
- The mixture water amount may be increased for easy application in horizontal applications.

CLEANING OF TOOLS

Used tools and equipment must be cleaned with water after the application. After **MasterTile® JF 565** is hardened, it can only be removed from the surface mechanically.

STANDARD COLORS

White
Grey

PACKAGING

5 kg and 20 kg polyethylene reinforced kraft bag

STORAGE

Store in an unopened, original container, under dry and cool conditions and protect against frost. For short term storage, do not stack more than 3 palletes on top of each other and dispatch them on a first come-first go basis. Palletes should not be stacked on each other on a long term basis.

SHELF LIFE

12 months in original unopened packaging if stored in appropriate conditions. Opened packagings should be consumed in one week.

HEALTH AND SAFETY PRECAUTIONS

It is dangerous to approach the application sites. During the application, a protective apparel, protective gloves, goggles and masks which comply with the Occupational Health and Safety Rules should be used. Due to the irritation effect of the uncured materials, the mixture should not come into contact with skin and eyes; in case of a contact, the affected area should be washed with plenty of water and soap; in case of swallowing, a physician should be consulted immediately. No food or beverages should be brought to the application area. The product should be stored and kept out of reach of children. For detailed information please consult the Material Safety Data Sheet.

DISCLAIMER

The technical information given in this publication is based on the present state of our best scientific and practical knowledge. **Master Builders Solutions Yapı Kimyasalları Sanayi ve Ticaret Ltd. Şti.** is only responsible for the quality of the product **Master Builders Solutions Yapı Kimyasalları Sanayi ve Ticaret Ltd. Şti.** is not responsible for results that may occur because the product is used other than advised and/or out of

MasterTile® JF 565

Cement Based Grouting with High Resistance Especially Designed for Swimming Pools

instructions regarding the place and the method of use.
This technical form is valid only till a new version is implemented and nullifies the old ones.

CONTACT INFORMATION

Master Builders Solutions Yapı Kimyasalları

Sanayi ve Ticaret Ltd. Şti.

Adres: Barbaros Mah. Begonya Sok.

Nidakule Kuzey Ataşehir, C Kapısı

No:3 E/5, 34746 Ataşehir İstanbul / Türkiye

Tel: 0216 217 88 00

Mail: mbs.tr@mbcc-group.com

Web: www.master-builders-solutions.com/tr-tr

® Registered trademark of a MBCC Group member in many countries of the world

MasterTile® JF 565 Technical Data Sheet -Revision Date: 01/2023

<h1>G</h1>	
FİRMA ADI / NAME OF THE LICENCE HOLDER MASTER BUILDERS SOLUTIONS YAPI KİMYASALLARI SANAYİ ve TİCARET LTD. ŞTİ.	
ADRES / ADDRESS BARBAROS MAH. BEGONYA SOK. NIDAKULE ATAŞEHİR KUZEY C KAPISI NO:3E/5 34746 ATAŞEHİR/İSTANBUL	
FABRİKA / MANUFACTURER GEBZE ORGANİZE SANAYİ BÖLGESİ 1000. SOKAK NO:1017 KOCAELİ	
YIL / DATE OF FIRST ISSUE OF LICENCE 20	
BELGE NO / REFERENCE NUMBER OF LICENCE 0300026 – TSE - 02 / 01	
STANDARD NO TS EN 13888	
ÜRÜN İSMİ/ PRODUCT NAME MASTERTILE JF 565	
TİP TÜR / TYPE: CG2WA Azaltılmış Su Emme ve Yüksek Aşınma Dayanımı, İlave Nitelikli Geliştirilmiş, Çimentolu Derz Dolgu Malzemesi / Improved cementitious grout with additional characteristics of reduced water absorption and high abrasion resistance	
Aşınma Direnci / Abrasion Resistance	≤1000 mm ³
Kuru depolamadan sonra eğilme dayanımı / Flexural strength after dry storage	≥2,5 N/mm ²
Donma-Çözünme çevriminden sonra eğilme dayanımı / Flexural strength after freeze-thaw cycles	≥2,5 N/mm ²
Kuru depolamadan sonra basınç dayanımı / Compressive strength after dry storage	≥15 N/mm ²
Donma-Çözünme çevriminden sonra basınç dayanımı / Compressive strength after freeze-thaw cycles	≥15 N/mm ²
Büzülme / Shrinkage	≤3 mm/m
Su emme, 30 dakika sonra / Water absorption after 30 min	≤2 g
Su emme, 240 dakika sonra / Water absorption after 240 min	≤5 g