


MasterSeal® Roof 2110




Crackbridging, waterproofing spray applied roofing system

Fields of application: the system is used in applications where no fire retardancy is required

	Primer	According to substrate. See technical data sheet MasterSeal M 800 or consult technical service	Consumption (approx):
	Liquid membrane	MasterSeal® M 800 Highly reactive, 2-component spray applied polyurethane waterproofing membrane	min. 2,3 kg/m ²
	Topcoat* 2 layers	MasterSeal® TC 259 Pigmented, single component, solvent-based, elastic, UV-and weather resistant PUR topcoat	2 x 0,1-0,15 kg/m ²
	Alternative Tocoat* 2 layers	MasterSeal® TC 258 Pigmented, single component, solvent-based, elastic, UV-and weather resistant PUR topcoat for use where a slip resistant finish is required by broadcasting with a mineral aggregate	2 x 0,25-0,5 kg/m ² Depending of size of aggregate

Hinweis: Consumptions are indicative and may be higher, depending on substrate roughness, temperature and porosity, as well as waste produced during application.

MasterSeal® Roof 2110



Crackbridging, waterproofing spray applied roofing system

Fields of application: the system is used in applications where no fire retardancy is required

DISCLAIMER

In view of widely varying site conditions and fields of application of our products, this technical data sheet is meant to provide general application guidelines only. This information is based on our present knowledge and experience. The customer is not released from the obligation to conduct careful testing of suitability and possible application for the intended use. The customer is obliged to contact the technical help-line for fields of application not expressly stated in the technical data sheet under "Fields of Application". Use of the product beyond the fields of application as stated in the technical data sheet without previous consultation with **Master Builders Solutions** and possible resulting damages are in the sole responsibility of the customer. All descriptions, drawings, photographs, data, ratios, weights i.e. stated herein can be changed without advance notice and do not represent the condition of the product as stipulated by contract. It is the sole responsibility of the recipient of our products to observe possible proprietary rights as well as existing laws and provisions. The reference of trade names of other companies is no recommendation and does not exclude the use of products of similar type. Our information only describes the quality of our products and services and is no warranty. Liability is accepted for incomplete or incorrect particulars in our data sheets only in the event of intent or gross negligence, without prejudice to claims under product liability laws.


CONTACT INFORMATION

**Master Builders Solutions Yapı Kimyasalları
Sanayi ve Ticaret Ltd. Şti.**

Adres: Barbaros Mah. Begonya Sok.
Nidakule Kuzey Ataşehir, C Kapsı
No:3 E/5, 34746 Ataşehir İstanbul / Türkiye
Tel: 0216 217 88 00
Mail: mbs.tr@mbcc-group.com
Web: www.master-builders-solutions.com/tr-tr

® Registered trademark of a MBCC Group member in many countries of the world

MasterSeal® Roof 2110 Technical Data Sheet -Revision
Date: 11/2020

	
1119 Master Builders Solutions Deutschland GmbH Donnerschweer Str. 372, D-26123 Oldenburg	
15	
480002	
EN 1504-2:2004	
Surface protection product - coatings EN 1504-2: ZA.1d, ZA.1e, ZA.1f and ZA.1g	
Abrasion resistance	NPD
Permeability to CO2	Sd > 50
Permeability to water vapour	Class I
Capillary absorption and permeability to water	< 0.01 kg/(m²xh0,5)
Thermal compatibility	≥ 1.5 N/mm²
Resistance to severe chemical attack	Reduction of hardness < 50 %
Crack bridging ability	Dynamic: B4.2: (23 °C) Static: A5: (23 °C)
Impact resistance	Class I
Adhesion strength by pull-off test	≥ 1.5 N/mm²
Reaction to fire	Efl
Artificial aging	NPD
Skid resistance	NPD