

Ucrete[®] MF

Heavy Duty Polyurethane Floor Finish

DESCRIPTION OF PRODUCT

Ucrete[®] MF is a unique HD Polyurethane resin floor with exceptional resistance to aggressive chemicals.

It provides a smooth protective floor finish suitable for applications in predominantly dry environments.

It is dense and impervious, providing the ideal floor finish for applications in the food, pharmaceutical and manufacturing industries including clean room, laboratory, packing hall and warehouse applications and wherever a robust, long lived floor is required.

Ucrete[®] Industrial Flooring has been widely used throughout the industry for more than 40 years; many of the older floors are still in service. A detailed project reference list is available upon request

PERFORMANCE DATA AIR QUALITY

Ucrete[®] has been awarded the Indoor Air Comfort Gold Label following extensive VOC emission chamber testing and auditing of quality management and production control procedures.

This demonstrates that **Ucrete[®]** is an extremely clean product without any volatile compounds that might taint food-stuff or affect the well-being of personnel.

All **Ucrete[®]** grades give very low emissions and conform to all the emissions requirements for indoor flooring systems in Europe including AgBB in Germany, Afsset in France, where they are rated A+ for VOC emissions (the cleanest rating), and M1 in Finland.

For further information please contact your local **Master Builders Solutions** representative.

TEMPERATURE RESISTANCE

A **Ucrete[®] MF** floor is fully resistant to liquid spillage and discharge up to 70°C. Suitable for freezer temperatures down to -15°C.

NON TAINING

Ucrete[®] MF is non tainting from the end of mixing, as tested by the Campden Technology Ltd.

CHEMICAL RESISTANCE

Ucrete[®] MF offers exceptional resistance to a wide range of chemical aggressors. For example **Ucrete[®]** is resistant to spillages of the following commonly encountered classes of chemicals:

Most dilute and concentrated organic acids such as, Acetic Acid, Lactic Acid, Oleic Acid and Citric Acid as commonly found in the food industry,

Dilute and concentrated acids: hydrochloric, nitric, phosphoric and sulphuric.

Dilute and concentrated alkalis, including sodium hydroxide to 50% concentration

Animal fats and vegetable oils, sugars flavourings and essences.

Mineral oils, kerosene, gasoline and brake fluids

A wide range of organic solvents including Methanol, Xylene, Ethers and Chlorinated solvents

Note: some staining or discolouration may occur with some chemicals, depending upon the nature of the spillage and the standards of housekeeping employed.

Extensive chemical resistance tables are available in the separate data sheet 'A guide to the chemical resistance of Ucrete Flooring'.

For detailed information, please contact your local **Master Builders Solutions** Construction Chemicals office for guidance.

IMPACT RESISTANCE

With high mechanical strengths and a low elastic modulus, **Ucrete[®] MF** is very resilient and able to withstand severe impact loads. While no material is indestructible and surface chipping may occur, brittle modes of failure resulting in cracking and disbondment are unknown with **Ucrete[®]** floors.

SUBSTRATE MOISTURE TOLERANCE

Ucrete[®] Industrial Flooring is extremely tolerant to residual substrate moisture and can be installed directly onto 7 day old concrete, or onto old good quality concretes with high moisture contents without the use of special primers, provided there is a functioning DPM within the structure.

This enables rapid construction programmes to be maintained and facilitates refurbishment work in wet process areas.

Epoxy surface DPMs should not be used as they soften under high temperature conditions and will lead to floor failure.

PERMEABILITY

Ucrete[®] MF exhibits zero absorption when tested to CP.BM2/67/2.

CLEANING & HYGIENE

Ucrete[®] flooring systems are accredited for use in facilities operating HACCP based food safety systems.

Ucrete[®] MF is cleaned using industry standard cleaning chemicals and equipment. The use of a food industry standard scrubber drier machine is recommended.

Tests undertaken by Campden Technology Ltd on the removal of Acinetobacter Calcoaceticus concluded that the cleanability of **Ucrete[®] MF** was comparable to stainless steel'

Regular cleaning and maintenance will enhance the life and appearance of any floor.

Detailed cleaning guidelines are available from your local **Master Builders Solutions** Construction Chemicals office.

Ucrete[®] MF

Heavy Duty Polyurethane Floor Finish

Typical Properties	
Density	1970 kg/m ³
Compressive strength (EN13892-2)	48-53 MPa
Tensile strength (BS6319 Part 7)	9 MPa
Flexural strength (EN13892-2)	18-21 MPa
Compressive modulus (BS 6319:Part 6)	3250-4000 MPa
Adhesive strength to concrete (EN13892-8)	Concrete failure
Coefficient of thermal expansion (ASTM C531:Part 4.05)	3.6 x 10 ⁻⁵ °C ⁻¹
Fire Testing (EN13501: Part 1)	BFL – S1

Note:- Samples cured for 28 days at 20°C

SLIP RESISTANCE

The **Ucrete[®] MF** floors have coefficient of friction as determined to EN13036 Part 4 with 4S rubber on the wet floor as follows:

Ucrete[®] MF 35

The **Ucrete MF** surface profiles conform to DIN51130 as follows:

Ucrete[®] MF R10 V -

Optimum slip resistance can only be maintained with regular cleaning.

COLOURS

Ucrete[®] MF is available in eight standard colours:

Red Yellow Green Orange
 Grey Cream Blue Green/Brown

Ucrete[®] floor systems have been formulated to provide the very highest chemical and heat resistance. As a direct result, some yellowing of the installed floor will occur in areas of direct UV exposure. This is most apparent in lighter colours.

SPECIFICATION

The floor finish shall be MF, from **Master Builders Solutions** plc, Construction Chemicals of 19 Broad Ground Road, Redditch, Worces-tershire, B98 8YP, installed at 4/6*mm in accordance with the manufacturer's instructions.

*(select as required)

SUBSTRATE QUALITY

Concrete substrates should be visibly dry and have a minimum tensile strength of 1.5 MPa.

Refer to the guide 'The Design & Preparation of Substrates for **Ucrete[®]** Industrial Flooring'

All joints in the substrate concrete subject to movement should be reflected through the **Ucrete[®]** floor and sealed with a suitable sealant.

APPLICATION CONDITIONS

For best results materials, substrate and air temperature should be in the range 15–25°C. Whilst **Ucrete[®] MF** will cure out effectively over a wide range of temperatures the optimum appearance is most readily achieved under good site conditions

Low temperatures will retard the setting and can impair the visual appearance of the floor.

High temperatures will shorten the open time and can impair the appearance of the floor.

Condensation and low temperatures can cause a white bloom on the surface.

COVERAGE

4mm: 8 - 10kg/m² 6mm: 12 - 14kg/m²

CURING

Normally **Ucrete[®] MF** floors can be put into service within 24 hours.

STORAGE

In covered warehouse conditions, above 5°C and below 30°C and out of direct sunlight. Materials must be raised off the floor and kept dry. Liquid components must be protected from frost.

DISPOSAL

Part 2 containers should be decontaminated with 5% sodium carbonate (washing soda) solution after use and disposed of as building waste in accordance with local regulations.

WARNINGS AND PRECAUTIONS

In its cured state **Ucrete[®]** is physiologically non-hazardous. For normal flooring applications **Ucrete[®]** does not require the use of respiratory protective equipment during installation.

Operatives should consult the CoSHH risk assessment and their work instructions.

Ucrete® MF

Heavy Duty Polyurethane Floor Finish

CONTACT INFORMATION

**Master Builders Solutions Yapı Kimyasalları
Sanayi ve Ticaret Ltd. Şti.**

Adres: Barbaros Mah. Begonya Sok.

Nidakule Kuzey Ataşehir, C Kapısı

No:3 E/5, 34746 Ataşehir İstanbul / Türkiye


Tel: 0216 217 88 00

Mail: mbs.tr@mbcc-group.com

Web: www.master-builders-solutions.com/tr-tr

® Registered trademark of a MBCC Group member in many countries of the world

Ucrete® MF Technical Data Sheet -Revision Date: 12/2020

	
1020	
Master Builders Solutions Yapı Kimyasalları Sanayi ve Ticaret Ltd. Şti. Adres: Barbaros Mah. Begonya Sok. Nidakule Kuzey Ataşehir, C Kapısı No:3 E/5, 34746 Ataşehir İstanbul	
20	
DOP NO: 04.13813.017	
EN 13813: 2002 SR-C50-F15-AR0,5-B2,0-IR30 Ucrete MF Şap malzemeleri ve zemine uygulanan şaplar (Screed material and floor screeds) Yüksek Performanslı, Düzgün Yüzey Bitişli Poliüretan Beton Kaplama (High Performance, Smooth Surface Finished Polyurethane Concrete Coating)	
Yangına Direnç (Reaction to Fire)	B _{FL} - S ₁
Basınç Dayanımı (Compressive Strength)	C50 N/mm ²
Eğilme Dayanımı (Flexural Strength)	F15 N/mm ²
Aşınma Direnci (Wear Resistance)	AR 0,5
Yapışma Dayanımı (Bond Strength)	B > 2,0 N/mm ²
Çarpmaya Direnç (Impact Resistance)	IR30 Nm deformasyon yok (IR30 Nm no deformation)

