

MasterFinish[®] RL 225

Water based chemical release agent

DESCRIPTION

A ready to use water based, safe, effective release agent which is friendly to the environment. **MasterFinish RL 225** is applied to mould and shutter faces prior to casting concrete in order to achieve a clean release. After removal of the formwork, the resultant concrete has a smooth, hard, uniform finish, with reduced incidence of blow holes. **MasterFinish RL 225** can be applied to the formwork by spray in the form of a light uniform mist coating.

PRIMARY USES

MasterFinish RL 225 is formulated for application to plywood, timber, steel and plastic faced formwork and moulds, prior to casting concrete, to ensure a clean release.

PACKAGING

MasterFinish RL 225 is available in 20 and 210 litre drums. Bulk deliveries available upon request.

TYPICAL PROPERTIES*

Colour	Milky liquid
SG finished product	0.971 at 25°C
Chloride content	<0.005%

COMPOSITION

A chemically active release agent blended with water.

DIRECTIONS FOR USE

Apply before the first casting and thereafter re-apply immediately after stripping and cleaning the mould.

Lightweight horticultural sprayers are ideal as **MasterFinish RL 225** is finely atomised to give a uniform coating. Excessive application should be avoided.

Alternatively, application may be made by a fine haired brush, only a very thin coating should be made and any excess removed.

If after the first application, the

MasterFinish RL 225 is completely absorbed into new timber or plywood, a further application should be made before filling the moulds or formwork.

ACTION

MasterFinish RL 225 reacts chemically with cement to impart excellent release properties to treated surfaces. Concrete cast against surfaces coated with **MasterFinish RL 225** exhibit a smooth, hard, uniform finish.

MasterFinish RL 225 has no negative effect on the properties of concrete nor will it impair the adhesion of subsequent surface treatments when applied at the recommended coverage rates.

COVERAGE

The coverage rate for **MasterFinish RL 225** is between 30 to 40m²/litre when spray applied depending on smoothness and porosity of the formwork used. Coverage is considerably enhanced on marine ply and steel faced forms.

Note:

Progressively better results are obtained on plywood and timber moulds as they become impregnated and the operatives become accustomed to working with the release agent. **MasterFinish RL 225** in general, may be used over timber moulds etc., which have been treated with other mould oils, providing excess has been removed.

EQUIPMENT CARE

MasterFinish RL 225 may usually be left in spray guns or sprayers without detriment, but with certain types, there may be some softening of rubber seals with prolonged contact.

MasterFinish® RL 225

STORAGE

Store under cover, out of direct sunlight and protect from extremes of temperature. Storage life up to 1 year when stored in unopened containers as above. The product must be stirred before being used.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult BASF's Technical Services Department.

SAFETY PRECAUTIONS

As with all chemical products care should be taken during use and storage to avoid contact with eyes and mouth. Treat splashes to eyes and skin immediately. If accidentally ingested, seek immediate medical attention. Keep away from children and animals. Reseal containers after use.

NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local MBCC representative.

MBCC reserves the right to have the true cause of any difficulty determined by accepted test methods.

QUALITY AND CARE

All products originating from MBCC's Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and OHSAS 18001.

* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the MBCC-Group in many countries.

MBCC_CC-UAE/MFinish_RL_225_01_00/v4/06_16

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this MBCC publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by MBCC either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not MBCC, are responsible for carrying out procedures appropriate to a specific application.

MB Construction Chemicals Solutions (T) Ltd
P.O. Box 23333, Dar Es Salaam, Tanzania
Tel: +255 699783912, Tel +255 769 777372
www.master-builders-solutions.com/en-tz

Disclaimer: the LRQA mark relates to certified management system and not to the product mentioned on this datasheet



MASTER®
BUILDERS
SOLUTIONS