

# MasterSeal® 590

Fast setting mortar to plug active water leaks in concrete and masonry

## DESCRIPTION

**MasterSeal 590** is a blend of hydraulic cements, well graded sands and additives supplied in dry powder form. It requires only the addition of clean water to produce a ready-to-use, ultra-rapid setting, plugging mortar.

## USES

- Stops active water or seepage under pressure through joints, cracks and holes in concrete or masonry, where a normal mortar would be washed away and resin would not bond.
- For sealing cracks and construction joints in reservoirs and other water-retaining structures.
- For instant sewer connections.
- For rapid anchoring of bolts, conduits, pipes, railings, sanitary equipment, etc.
- Joint filling, pointing between concrete segments in concrete and brick tunnels, sewage systems, pipes and mines.

## BENEFITS

### Durable

- Chloride-free, will not promote corrosion of reinforcement.
- Expands as it sets to ensure a permanent watertight seal.
- Mechanical characteristics similar to concrete.

### Cost effective

- Ultra-rapid setting for instant leak plugging.
- Blocks water, no injection equipment required.

### Easy to apply

- Only to be mixed with water.

### Environmentally friendly

- Cement based, contains no toxic elements.

## PACKAGING

5 kg can and 25 kg pail.

## COLOURS

Standard: grey.

## TYPICAL PHYSICAL PROPERTIES\*

**Typical values. All tests were carried out under temperature controlled conditions of 21°C.**

Maximum particle size		0.8 mm
Mechanical strengths		N/mm <sup>2</sup>
Compressive	30 min.	13.8
	24 h.	31.0
	7 d.	44.3
	28 d.	52.8
Tensile	28 d.	3.3
Flexural	30 min.	2.7
	24 h.	6.1
	7 d.	6.3
	28 d.	7.0

## COVERAGE

1 kg of powder will fill 585 cm<sup>3</sup> or a joint 20mm x 20mm x 1.45 m  
approx. 1.7 kg powder / dm<sup>3</sup>

## STORAGE

All materials are to be stored under cover, clear of the ground and stacked not more than 2 pails high. Protect the materials from all sources of moisture and frost. Rotate stock in order not to exceed the shelf life of 12 months. Once opened the material should be used as soon as possible.

## APPLICATION

### Substrate preparation

Preferably, cracks or holes should be cut to a minimum width and depth of 20 mm, cutting the sides as square as practicable. Undercut if possible. Avoid leaving a V section. Do not feather-edge.

### For plugging active leaks

Cut out the opening to a minimum diameter of 20 mm or till a sound base is obtained.

# MasterSeal<sup>®</sup> 590

---

## **For sealing the wall / floor joint in an existing Construction**

Cut out the joint/crack at least 20 mm wide and deep, cutting back into the wall slightly.

## **For sealing the wall / floor joint in a new construction**

When designing, foresee an opening situated at the wall/floor joint (20 mm x 20 mm) to be filled with **MasterSeal 590**.

## **To repair mortar joints and cracks in masonry walls, or cracks in concrete walls.**

Cut out the defective mortar joints or cracks to a minimum width and depth of 20 mm. Undercut if possible.

## **For holes, patches, honeycomb and other construction faults in concrete walls.**

Remove all tie wires, wood or foreign objects by cutting back the concrete from the surface to a depth of 25 mm.

## **For anchoring bolts or metal posts in concrete or masonry\*.**

Drill a hole deep enough to secure the bolt or post properly and large enough so there is at least 10 mm on all sides of it.

Flush out holes, joints or cracks with water to remove all loose particles and dust. All surfaces must be dampened with clean water immediately prior to the application of **MasterSeal 590**.

### **MIXING**

**Wet density** 2.14 kg/dm<sup>3</sup>

**Final setting time** 2 – 3 minutes

#### **Mixing liquid**

± 0.26 (0.24 – 0.28) litres clean water for 1 kg of Powder

**MasterSeal 590** powder should be mixed with clean water by hand only. Mix quickly and well to a stiff consistency using ± 0.26 litres water for 1kg of powder. Do not overmix.

Do not mix more than can be placed within one application, 1 - 2 minutes (at 20°C). Do not re-temper.

## **Application**

### **For plugging active leaks**

Form a plug of the mixed material in the gloved hand until slight setting occurs. Then press **MasterSeal 590** mortar firmly into the opening; exert full pressure, without moving the hand. Hold in place for approximately 60 seconds.

If the opening is too big to be closed with 1 mix of **MasterSeal 590**, work progressively from the sides to the middle, following the above procedure.

After setting, but not completely hardened, trim off excess material in order to create a uniform level with the surrounding surfaces. Remove from centre to sides.

## **For sealing the wall / floor joint in an existing construction**

Fill the opening with **MasterSeal 590** mortar, force into place forming a cove.

## **For sealing the wall / floor joint in a new construction**

Fill the rebate with **MasterSeal 590** mortar, force into place forming a cove.

## **To repair mortar joints and cracks in masonry walls, or cracks in concrete walls.**

Trowel or press into the joint.

## **For holes, patches, honeycomb and other construction faults in concrete walls.**

Fill all holes, patches, honeycombing and other construction faults.

## **For anchoring bolts or metal posts in concrete or masonry\*.**

Fill the hole with a putty-like consistent mortar and tamp it down so that the entire hole is full. Immediately centre the bolt or post over the hole and force it into the **MasterSeal 590** mortar.

# MasterSeal® 590

Tamp the **MasterSeal 590** mortar firmly around the bolt or post.

## CURING

Once the placed **MasterSeal 590** mortar has stiffened sufficiently, dampen with clean water and maintain in a damp condition for a minimum of 15 minutes.

## CLEAN UP AND SPILLAGES

Not hardened material may simply be removed with water.

## HEALTH AND SAFETY

**MasterSeal 590** is based on cement and thus can be irritating to the skin and eyes. Gloves and eye protection should be worn. The use of dust masks is recommended.

Accidental splashes of the material to the skin or eyes should be immediately washed off with clean water. In the event of prolonged irritation seek medical advice. In the case of ingestion give water or milk to drink and treat symptomatically. Medical advice should be sought.

A Material Safety Data Sheet for this product is available on request.

## NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local MBCC representative.

MBCC reserves the right to have the true cause of any difficulty determined by accepted test methods.

## QUALITY AND CARE

All products originating from MBCC's Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and OHSAS 18001.

\* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the MBCC-Group in many countries.

MBCC\_CC-UAE/SI\_590\_10\_06/v2/05\_14

## STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this MBCC publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

## NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by MBCC either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not MBCC, are responsible for carrying out procedures appropriate to a specific application.