

# MasterSeal<sup>®</sup> 911

## Adhesive for MasterSeal 910

### DESCRIPTION

**MasterSeal 911** is a one component adhesive, based on a modified silane polymer used to secure the **MasterSeal 910** swelling gasket to all common substrates in construction.

### FEATURES

- Adheres the gasket on plane and rough surface.
- Excellent tack on dry and humid surface.
- Hardened adhesive remains highly flexible in humid and wet environment.

### APPLICATION PROCEDURE

- Punch relief hole into top of cartridge.
- Cut nozzle (approx. opening 5mm).
- Insert cartridge into standard caulking gun.
- Apply adhesive under angle of ~45° on substrate.
- Fix **MasterSeal 910** into Adhesive within 10 minutes.

### PACKAGING

**MasterSeal 911** is supplied in 290ml cartridges.

### \*TYPICAL PROPERTIES

Colour	White
Density	~1.5
Odour	None
Consistency	Paste
Content of solids	100%
Hardening system	Humidity
Hardening velocity (DIN 50014)	4mm / 24 hours
Skin over (DIN 50014)	20 minutes
Shore Hardness A (DIN 53504)	~ 27
Tensile strength (DIN 53504)	~0.9MPa
Elongation at break (DIN 53504)	~300%
Temperature at application	5-40°C
Temperature of service	-30° to +80°C
Storage / Storage temperature	Avoid frost, 10-25°C

### COVERAGE

1 cartridge per 10m (plane surface)

### STORAGE

Store in a well enclosed, cool and dry place.

### SHELF LIFE

**MasterSeal 911** has a shelf life of 12 months if stored in a well enclosed, cool and dry place.

\* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the MBCC-Group in many countries.

# MasterSeal® 911

---

MBCC\_CC-UAE/SI\_911\_03\_02/v1/12\_13

---

## STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this MBCC publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

---

## NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by MBCC either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not MBCC, are responsible for carrying out procedures appropriate to a specific application.

---

MB Construction Chemicals Solutions (T) Ltd  
P.O. Box 23333, Dar Es Salaam, Tanzania  
Tel: +255 699783912, Tel +255 769 777372  
[www.master-builders-solutions.com/en-tz](http://www.master-builders-solutions.com/en-tz)

**Disclaimer:** the LRQA mark relates to certified management system and not to the product mentioned on this datasheet



**MASTER®**  
**» BUILDERS**  
SOLUTIONS