

Installation Guide

RELATED DOCUMENTS

MasterFlow 713 Technical Data Guide



MasterFlow[®] 713

High-precision non-shrink mineral-aggregate grout

HOW TO APPLY

SURFACE PREPARATION

1. Steel surfaces must be free of dirt, oil, grease, or other contaminants.
2. The surface to be grouted must be clean, SSD, strong, and roughened to a CSP of 5–9 following ICRI Guideline 310.2 to permit proper bond.
3. When dynamic, shear or tensile forces are anticipated, concrete surfaces should be chipped with a “chisel-point” hammer, to a roughness of (plus or minus) $\frac{3}{8}$ " (10 mm). Verify the absence of bruising following ICRI Guideline 210.3.
4. Concrete surfaces should be saturated (ponded) with clean water for 24 hours just before grouting.
5. All freestanding water must be removed from the foundation and bolt holes immediately before grouting.
6. Anchor bolt holes must be grouted and sufficiently set before the major portion of the grout is placed.
7. Shade the foundation from sunlight 24 hours before and 24 hours after grouting.

FORMING

1. Forms should be liquid tight and nonabsorbent. Seal forms with putty, sealant, caulk or polyurethane foam. Use sufficient bracing to prevent the grout from leaking or moving.
2. Moderately sized equipment should utilize a head box to enhance the grout placement.
3. Side and end forms should be a minimum 1" (25 mm) distant horizontally from the equipment to be grouted to permit expulsion of air and any remaining saturation water as the grout is placed.
4. Leave a minimum of 2" between the bearing plate and the form to allow for ease of placement.
5. Eliminate large, non-supported grout areas wherever possible.
6. Extend forms a minimum of 1" (25 mm) higher than the bottom of the equipment being grouted.
7. Expansion joints may be necessary. Consult your local Master Builders Solutions field representative for suggestions and recommendations.

TEMPERATURE

1. For non-shrink grouting, store and mix grout to produce the desired mixed-grout temperature based upon ambient temperatures and jobsite conditions.
2. If temperature extremes are anticipated or if special placement procedures are planned, contact your local Master Builders Solutions representative for assistance.
3. When grouting at minimum temperatures, see that foundation, plate, and grout temperatures do not fall below 50° F (10° C) until after final set. Protect the grout from freezing (32° F or 0° C) until it has attained a compressive strength of 3,000 psi (20.7 MPa) in accordance with ASTM C 109.

Recommended Temperature Guidelines for Nonshrink Grouting

	MINIMUM ° F (° C)	PREFERRED ° F (° C)	MAXIMUM ° F (° C)
Foundation and plates	45 (7)	50–80 (10–27)	90 (32)
Mixing water	45 (7)	50–80 (10–27)	90 (32)
Grout at mixed and placed temp.	45 (7)	50–90 (10–32)	90 (32)

MIXING

By using the minimum amount of water to provide the desired workability, maximum strength will be achieved. Whenever possible, mix the grout with a mortar mixer or an electric drill with a paddle such as ICRI 320.5 type A, D, E, F, G or H. Put the measured amount of potable water into the mixer, add grout, then mix till a uniform consistency is attained. Do not use water in an amount or a temperature that will cause bleeding or segregation.

NOTE: The water requirement may vary due to mixing efficiency, temperature, and other variables.

1. Add the minimum potable or ASTM C1602-compliant water to the mixer, then slowly add the MasterFlow 713, while mixing.
2. The water demand will depend on mixing efficiency and material and the ambient temperature. Use the minimum amount of water required to achieve the necessary placement consistency. Recommended flow is 25–30 seconds or greater using the ASTM C 939 Flow-Cone Method. Before placing grout at ambient temperatures below 50° F (10° C) and above 80° F (26° C), consult your Master Builders Solutions representative.
3. Moderate size batches of grout are best mixed in one or more clean mortar mixers.
4. Mix grout a minimum of 3 minutes after all material and water are in the mixer.
5. Do not mix more grout than can be placed in approximately 10 minutes or less, depending on ambient temperatures.
6. Transport by wheelbarrow or buckets or pump to the equipment being grouted. Minimize the transporting distance.
7. Do not retemper grout by adding water.
8. For placements greater than 6" (152 mm) in depth, product should be extended with aggregate. Aggregate extension is dependent upon the grout type, placement, application requirements, and is typically required for placement depths beyond the limitation of the neat material. The aggregate should be washed, graded, saturated, surface-dry (SSD), high-density, free from deleterious materials, and comply with the requirements of ASTM C 33. Consult Master Builders Solutions Technical Service for additional guidance.

PLACEMENT

1. Place MasterFlow 713 in a continuous pour. Discard grout that becomes unworkable. Make sure that the grout fills the entire space being grouted and remains in contact with the plate throughout the entire grouting process.
2. Immediately after placement, trim the surfaces with a trowel and cover the exposed grout with clean wet rags. Keep the rags wet for 5–6 hours.
3. The grout should offer stiff resistance to penetration with a pointed mason's trowel before the grout forms are removed or excessive grout is cut back.
4. To further minimize the potential moisture loss within the grout, cure all exposed grout with an approved membrane curing compound (compliant with ASTM C 309 or preferably ASTM C 1315) immediately after the wet rags are removed.
5. DO NOT VIBRATE GROUT. Steel straps inserted under the plate may be used to help move the grout.
6. Consult your Master Builders Solutions representative before placing lifts more than 6" (152 mm) in depth.

CURING

Cure all exposed grout with an approved membrane curing compound compliant with ASTM C 309 or preferably ASTM C 1315. Apply curing compound immediately after the wet rags are removed to minimize potential moisture loss.

HEALTH, SAFETY AND ENVIRONMENTAL

Read, understand and follow all Safety Data Sheets and product label information for this product prior to use. The SDS can be obtained by visiting www.master-builders-solutions.com/en-us, e-mailing your request to mbsbscst@mbcc-group.com or calling 1(800)433-9517. Use only as directed.

IN CASE OF EMERGENCY: Call CHEMTEL +1 (800) 255-3924 or if outside the US or Canada, +1 (813) 248-0585.

WASTE DISPOSAL METHOD

This product when discarded or disposed of, is not listed as a hazardous waste in federal regulations. Dispose of in a landfill in accordance with local regulations. For additional information on personal protective equipment, first aid, and emergency procedures, refer to the product Safety Data Sheet (SDS) on the job site or contact the company at the address or phone numbers given below.

LIMITED WARRANTY NOTICE

Master Builders Solutions Construction Systems US, LLC (“Master Builders”) warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. MASTER BUILDERS MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is shipment to purchaser of product equal to the amount of product that fails to meet this warranty or refund of the original purchase price of product that fails to meet this warranty, at the sole option of Master Builders. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. MASTER BUILDERS WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on Master Builders’ present knowledge and experience. However, Master Builders assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. Master Builders reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.

FOR PROFESSIONAL USE ONLY. NOT FOR SALE TO OR USE BY THE GENERAL PUBLIC.