

# MasterProtect<sup>®</sup> 100CR

## Sprayable chemical-resistant epoxy coating

FORMERLY SEWER GUARD<sup>®</sup> HBS 100 EPOXY LINER

### PACKAGING

4 gal (15 L) kits

Part A - 2 gallons

Part B - 2 gallons

### COLOR

Gray

### YIELD

16 ft<sup>2</sup>/gal (0.4 m<sup>2</sup>/L) at 100 mils (WFT)

### STORAGE

Store and transport in unopened containers in a cool, clean, dry area. Keep from freezing.

### SHELF LIFE

2 years when properly stored

### VOC CONTENT

1.5 g/L less water and exempt solvents when components are mixed and applied per Manufacturer's instructions

### DESCRIPTION

MasterProtect 100CR is a 100% solids, sprayable, high-build chemical-resistant epoxy coating. It is used to provide resistance to hydrogen sulfide attack in the water and sewage-treatment industries. MasterProtect 100CR eliminates the need for prefabricated or cast-in-place manhole liners.

### PRODUCT HIGHLIGHTS

- High-build material, sprayable up to 80 mils thick
- Epoxy chemistry for excellent resistance to hydrogen sulfide and many industrial chemicals; high bond strength
- Moisture insensitive, cures well in damp environments
- Low odor, suitable for application in confined spaces
- 100% solids, meets all federal and state VOC regulations

### APPLICATIONS

- Vertical and overhead surfaces
- Nontraffic-bearing horizontal surfaces
- Interior and exterior below grade
- Applications requiring resistance to hydrogen sulfide
- Rehabilitating manholes
- Lining large diameter pipes
- Lift stations and pumping stations

### SUBSTRATES

- Concrete
- Masonry

### HOW TO APPLY

#### SURFACE PREPARATION

#### CURED CONCRETE

1. Surface must be clean, structurally sound, and fully cured 28 days.
2. Remove any loose or unsound brick or concrete.
3. Surface must be entirely free of oil, grease, paint, detergent, rust, laitance, or other surface contaminants. Surfaces can be damp but must be free of standing water.
4. Abrade the surface by abrasive blasting or other mechanical scarification techniques to profile of ICRI CSP 4. Water blasting is not recommended.
5. For full surface restoration ½–4" (13–102 mm) deep, use MasterEmaco S 488CI. Trowel or spray MasterEmaco S 488CI onto prepared surface and finish with a wood or plastic float.
6. Allow the MasterEmaco S 488CI to cure a minimum of 4 hours at 70 °F (21 °C) before applying MasterProtect 100CR. If the MasterEmaco S 488CI cures for more than 12 hours, scarify surface to remove all laitance and prime the MasterEmaco S 488CI with MasterEmaco P 130 before applying a coat of MasterProtect 100CR.

**Technical Data**

**Composition**

MasterProtect 100CR is a 100% solids cyclo-aliphatic amine-cured epoxy coating.

**Typical Properties**

PROPERTY	VALUE
<b>Pot life</b> , approx min, 4 gallons mixed, at 75 °F (24 °C)	20
<b>Mixing ratio</b> , by volume (Part A to B)	1 to 1
<b>Tack-free time</b> , hrs, at 75 °F (22 °C)	3-5
<b>Final cure</b> , days	7

**Test Data**

PROPERTY	RESULTS	TEST METHOD
<b>Mixed viscosity</b> , cps, #6 spindle, 50 rpm	9,000-11,000	Brookfield
<b>Adhesion to dry or damp concrete</b> , psi (MPa)	350 (2.4); minimum substrate failure	ASTM D 4541
<b>Adhesion to MasterEmaco S 488CI</b> , psi (MPa)	resulted in substrate failure	ASTM D 4541
<b>Tensile strength</b> , psi (MPa)	3,000 (20.7)	ASTM D 638
<b>Compressive strength</b> , psi (MPa)	8,500 (58.6)	ASTM D 695
<b>Hardness</b> , Shore D	78	ASTM D 2240
<b>Tensile elongation</b> , %	3	ASTM D 638
<b>Compressive modulus</b> , psi (MPa)	5 × 10 <sup>5</sup> (3,400)	ASTM D 695
<b>Flexural strength</b> , psi (MPa)	4,300 (29.6)	ASTM C 580
<b>Flexural modulus</b> , psi (MPa)	3.5 × 10 <sup>5</sup> (2,400)	ASTM C 580
<b>Weight change</b> , after 1 year		
Sulfuric acid concentration	%	
pH 1	0.7	
pH 2	0.3	
pH 3	0.3	

All application and performance values are typical for the material, but may vary with test methods, conditions, and configurations.

**Chemical Resistance**

Specimens cured 7 days at 75 °F (24 °C); 1 month immersion time

CHEMICAL	RESULTS
Bleach	Resistant*
Detergent	Resistant
Gasoline	Resistant
Sodium chloride (20% solution)	Resistant
Sodium hydroxide (20% solution)	Resistant
Sulfuric acid (5% solution)	Resistant
Sulfuric acid (10% solution)	Resistant

\*Defined as no severe color change or deterioration of the samples.

#### MIXING

1. Precondition all components to 70 °F (21 °C) for 24 hours before using.
2. If using a conventional airless sprayer, mix each component separately, then pour equal volumes of Part A and Part B into a clean pail. Scrape sides of containers to ensure correct mixing ratios.
3. Do not mix more material than is sprayable within the pot life of the mixed material. (approximately 20 minutes at 70 °F)
4. Mix Part A and B together thoroughly for about 3 minutes using a slow-speed mechanical mixer to obtain a uniform color.

#### PRIMING

Prime surface with MasterEmaco P 130. Apply MasterProtect 100CR after the primer has become tack free (Approximately 3–5 hours at 70 °F [21 °C]). Recoat with MasterProtect 100CR no later than 24 hours after priming with MasterEmaco P 130.

#### APPLICATION

##### SPRAY APPLICATION

1. Spray apply with a Graco® HydraMax™ 350 (4,000 psi) airless sprayer or equivalent. Use a high-pressure spray hose with an I.D. of 3/8" and a Graco® Flex Plus gun with a heavy-duty RAC tip (0.025–0.031).
2. For moderate chemical conditions, apply MasterProtect 100CR at 30 mils (0.76 mm) at approximately 50 ft<sup>2</sup>/gallon (1.3 m<sup>2</sup>/L).
3. Harsh chemical environments require thicker applications at 80–125 mils (2.0–3.2 mm). Two coats may be required to achieve a void-free film on very porous surfaces.
4. Do not use this product if the air, substrate, or material temperature is below 45 °F (7 °C) or expected to fall below 45 °F (7 °C) within 12 hours of application.

##### ROLLER APPLICATION

Use a 1/4" (6 mm) nap synthetic roller. Only mix enough material that can be applied within 20 minutes. Be aware that spraying is the preferred method of application.

##### RECOATING MASTERPROTECT 100CR

Recoat within 24 hours at 70 °F (21 °C). After 24 hours, mechanically abrade the entire surface of the coating and clean with acetone or MEK. Allow MasterProtect 100CR to dry and reapply coating within 1 hour.

#### CLEAN UP

Purge the airless system with xylene before material has time to set. Cured material must be removed mechanically.

#### FOR BEST PERFORMANCE

- Do not use this product if the air, substrate, or material temperature is below 45 °F (7 °C) or expected to fall below 45 °F (7 °C) within 12 hours.
- Temperature variations affect nonsag properties of this product. Higher temperatures may cause the product to sag; lower temperatures will decrease workability of product by causing it to thicken.
- Do not thin; solvents will prevent proper curing.
- For professional use only; not for sale to or use by the general public.
- Make certain the most current versions of product data sheet and SDS are being used; visit [www.master-builders-solutions.com/en-us](http://www.master-builders-solutions.com/en-us) to verify the most current version.
- Proper application is the responsibility of the user. Field visits by Master Builders Solutions personnel are for the purpose of making technical recommendations only and are not for supervising or providing quality control on the jobsite.

#### HEALTH, SAFETY AND ENVIRONMENTAL

Read, understand and follow all Safety Data Sheets and product label information for this product prior to use. The SDS can be obtained by visiting [www.master-builders-solutions.com/en-us](http://www.master-builders-solutions.com/en-us), e-mailing your request to [mbsbscst@mbcc-group.com](mailto:mbsbscst@mbcc-group.com) or calling 1(800)433-9517. Use only as directed.

**IN CASE OF EMERGENCY: Call CHEMTEL +1 (800) 255-3924 or if outside the US or Canada, +1 (813) 248-0585.**

#### LIMITED WARRANTY NOTICE

Master Builders Solutions Construction Systems US, LLC ("Master Builders") warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. MASTER BUILDERS MAKES NO

OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is shipment to purchaser of product equal to the amount of product that fails to meet this warranty or refund of the original purchase price of product that fails to meet this warranty, at the sole option of Master Builders. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. MASTER BUILDERS WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on Master Builders' present knowledge and experience. However, Master Builders assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. Master Builders reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.

**FOR PROFESSIONAL USE ONLY. NOT FOR SALE TO OR USE BY THE GENERAL PUBLIC.**