

MasterProtect® HB 400

Water-based, high-build, 100% acrylic waterproof coating

FORMERLY THOROCCOAT®

PACKAGING

5 gallon (18.9 L) pails

YIELD

See charts on page 3

STORAGE

Store in unopened containers in a clean, dry area. Keep from freezing

SHELF LIFE

18 months when properly stored

VOC CONTENT

Less than 100 g/L
less water and exempt solvents

DESCRIPTION

MasterProtect HB 400 is a water-based, high-build, 100% acrylic waterproof coating for above-grade concrete, masonry, stucco and EIFS.

PRODUCT HIGHLIGHTS

- Available in a broad range of colors and textures for design versatility
- Resists wind-driven rain, helps prevent water penetration into the substrate
- Breathable to allow water vapor to escape
- Excellent adhesion, bonds securely to substrate for long-term durability
- UV resistance provides excellent color retention for a long lasting attractive finish
- Excellent hiding power
- Textured formulations help improve aesthetics of irregular substrates
- Effective carbon dioxide diffusion barrier, protects embedded steel from corrosion
- Freeze/thaw resistant, suitable for cold climates
- Low VOC content for broad compliance across all regions

APPLICATIONS

- Exterior
- Vertical and overhead surfaces
- Above-grade
- Protecting and waterproofing

SUBSTRATES

- Concrete
- Masonry
- Cement plaster
- Stucco
- EIFS
- Existing Coatings

HOW TO APPLY

SURFACE PREPARATION

1. Surfaces should be clean and sound and free of all bond-inhibiting contaminants.
2. Concrete substrates should be fully cured.
3. Repair any holes, spalled and damaged concrete with appropriate Master Builders Solutions repair materials. Allow appropriate cure time prior to coating.
4. Remove any protruding concrete accessories and smooth out any surface irregularities.
5. High-pressure power wash surface (or abrasive blast on hard, dense surfaces) to create a profile of SP 3, per ICRI Guide 310.2.
6. Some stains may require chemical removal. Neutralize any cleaning compounds used and rinse with clean water.
7. Check adhesion of old coatings according to ASTM D 3359, Measuring Adhesion by Tape Test Method A.
8. Remove any blisters or delaminated areas and sand edges to smooth rough areas and provide transition to old paint areas.

Technical Data

Composition

MasterProtect HB 400 is a water-based, high-build, 100% acrylic waterproof coating.

Compliances

- Alberta Transportation - Type 3 sealer

Test Data

MASTERPROTECT HB 400 SMOOTH

PROPERTY	RESULTS	TEST METHOD
Density, lbs/gal (kg/L)	11.4–12.4 (1.37–1.49)	ASTM D 1475
Solids, %		ASTM D 5201
By weight	56.2	
By volume	38	
Viscosity, KU	102–110	ASTM D 562 (Stormer)

MASTERPROTECT HB 400 FINE

PROPERTY	RESULTS	TEST METHOD
Density, lbs/gal (kg/L)	13.1–14.1 (1.57–1.69)	ASTM D 1475
Solids, %		ASTM D 5201
By weight	68.6	
By volume	49	
Viscosity, KU	117–125	ASTM D 562 (Stormer)
Gloss, gloss units	<3	ASTM D 523

MASTERPROTECT HB 400 COARSE

PROPERTY	RESULTS	TEST METHOD
Density, lbs/gal (kg/L)	13.2–14.2 (1.58–1.70)	ASTM D 1475
Solids, %		ASTM D 5201
By weight	69.9	
By volume	50	
Viscosity, KU	117–125	ASTM D 562 (Stormer)

MASTERPROTECT HB 400 SMOOTH

PROPERTY	RESULTS	TEST METHOD
Resistance to wind-driven rain	Meets requirement – no water penetration	TT-C-555B
Accelerated weathering, 5,000 hrs	Passes	ASTM G 23, Type D
Visual color change, 5,000 hrs	Passes	ASTM D 1729
Chalking, 5,000 hrs	Passes	ASTM D 4214
Freeze/thaw resistance, 50 cycles	Passed	DOT Method A and B
Water-vapor permeance, perms	23	ASTM D 1653
Moisture resistance,	Meets requirement: no blistering, loss of adhesion, or discoloration	TT-C-555B

Test Data

MASTERPROTECT HB 400 SMOOTH, CONTINUED

PROPERTY	RESULTS	TEST METHOD
Salt spray (fog) resistance, 300 hrs	Passed	ASTM B 117
Carbon-dioxide diffusion		PR EN 1062-6
R (equivalent air-layer thickness), ft (m)	1,318 (402)	
Sc (equivalent concrete thickness),in (cm)	39 (100)	
Flexibility, 1" mandrel	No cracking	ASTM D 522
Dirt pick-up, % after 6 months exposure	92.02; passed	ASTM D 3719
Sand abrasion resistance, at 3,000 L	Passed	ASTM D 968 Method A
Impact resistance, at 30 in-lbs	Passed	ASTM D 2794
Fungus resistance	No growth Meets requirement	ASTM D 3273
Mildew resistance		Fed Spec. TT-P-29 (Fed. Std. 141, Method 6152 and 6271.1)
Aspergillus oryzae, 7 days	No growth	
Aspergillus niger, 21 days	No growth	
Surface burning characteristics		ASTM E 84
Flame spread	1	
Smoke	4	
Fuel contribution	7	
Flash point, °F (°C)	> 200 (93)	ASTM D 56 Tag Closed Tester
Algae resistance	No growth	ASTM D 5589

Test results are averages obtained under laboratory conditions. Reasonable variations can be expected.

Yield

TEXTURE	RATE, FT ² /GAL/COAT (M ² /L)	WET FILM, MILS (MM)	DRY FILM, MILS (MM)
Smooth Recoat	75–125 (1.84–2.45)	22–13 (0.559–0.33)	8–5 (0.203–0.127)
Fine or Coarse Recoat	75–125 (1.84–2.45)	22–13 (0.559–0.33)	11–6 (0.279–0.152)
Smooth	75–100 (1.84–2.46)	22–16 (0.559–0.406)	8–6 (0.203–0.152)
Fine or Coarse	75–100 (1.84–2.46)	22–16 (0.559–0.406)	11–8 (0.279–0.203)

*Coverages are estimates for smooth, dense concrete. Coverages will vary on porous or textured surfaces.

9. Treat cracks greater than 1/32" with MasterProtect FL 746 or MasterProtect FL 748. Treat cracks larger than 1/4" as expansion joints and fill with appropriate Master Builders Solutions sealant.
10. New CMU must have a base coat of MasterProtect FL 749.

MIXING INSTRUCTIONS

1. Prior to use, mix MasterProtect HB 400 at slow speed with drill and mixing paddle to ensure uniform color and aggregate disbursement and to minimize air entrapment.

2. In multi-pail applications, mix the contents of each new pail into the partially used previous pail to ensure color consistency and smooth transitions from pail to pail.

APPLICATION

1. MasterProtect HB 400 is meant to be applied as a two-coat system, achieving a total dry-film thickness (DFT) of 12–16 mils (0.3 mm–0.4 mm). For re-coat applications one coat applied at 11–5 mils (0.279–0.127) DFT.
2. Apply MasterProtect HB 400 by brush, spray, roller, or spray-and-backroll. Spray apply

- MasterProtect HB 400 Coarse for best results.
3. Maintain proper uniform wet-film thickness (WFT) during application to ensure the performance characteristics desired (see yield rates section).
4. Always work to a natural break and maintain a wet edge during application.
5. For uniformity of color and texture, application techniques must be consistent throughout the project.
6. For horizontal applications, please contact your local Master Builders Solutions representative.

ROLLER

1. Use a quality ¾"– 1-1/4" nap roller cover.
2. Completely saturate the roller and keep it loaded with the coating to build the required mils. Never dry roll.
3. Cross roll, maintaining a wet edge, to achieve uniform thickness. Backroll in one direction for consistent appearance.

SPRAY

1. Equipment is available for spraying all grades of MasterProtect HB 400. For fine and coarse textures, it is necessary to use a heavy-duty sprayer designed for the application of coatings that contain sand particles. Contact equipment manufacturer for further recommendations.
2. For smooth and fine grades, backrolling in one direction after spray application is recommended to achieve uniform texture and film thickness.

BRUSH

1. Application by brush is recommended only for small inaccessible areas, e.g., on touch-ups.
2. Use only a nylon brush.

DRYING TIME

Times assume 70 °F (21 °C) and 50% relative humidity.

To touch: 1–2 hours

To recoat: minimum of 6 hours

Lower surface or air temperatures and higher relative humidity will extend the drying time.

CLEAN UP

Clean all tools and equipment immediately with water. Cured material may be removed by mechanical means.

FOR BEST PERFORMANCE

- Do not apply when substrate or ambient temperature is 40 °F (4 °C) or below or is expected to fall below 40 °F (4 °C) within 24 hours after application.
- Do not apply if rain is expected within 24 hours of application.
- Not for immersion service.
- Apply a 4 by 4 ft (1.2 by 1.2 m) test area to verify acceptable color, texture and adhesion before proceeding with any project. The test method for measuring adhesion is ASTM D

3359, Measuring Adhesion by Tape Method A. On the 0–5 scale, a minimum adhesion rating of 4A is required.

- Color formulas containing organic colorants are susceptible to fading in exterior applications. Refer to Technical Support for guidance.
- Do not thin the material.
- For professional use only; not for sale to or use by the general public.
- Make certain the most current versions of product data sheet and SDS are being used; visit www.master-builders-solutions.com/en-us to verify the most current versions.
- For horizontal applications, please contact your local Master Builders Solutions representative.
- Proper application is the responsibility of the user. Field visits by Master Builders Solutions personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.

HEALTH, SAFETY AND ENVIRONMENTAL

Read, understand and follow all Safety Data Sheets and product label information for this product prior to use. The SDS can be obtained by visiting www.master-builders-solutions.com/en-us, e-mailing your request to mbsbscst@mbcc-group.com or calling 1(800)433-9517. Use only as directed.

IN CASE OF EMERGENCY: Call CHEMTEL +1 (800) 255-3924 or if outside the US or Canada, +1 (813) 248-0585

LIMITED WARRANTY NOTICE

Master Builders Solutions Construction Systems US, LLC ("Master Builders") warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. MASTER BUILDERS MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product,

including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is shipment to purchaser of product equal to the amount of product that fails to meet this warranty or refund of the original purchase price of product that fails to meet this warranty, at the sole option of Master Builders. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. MASTER BUILDERS WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on Master Builders Solutions's present knowledge and experience. However, Master Builders Solutions assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. Master Builders Solutions reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.

FOR PROFESSIONAL USE ONLY. NOT FOR SALE TO OR USE BY THE GENERAL PUBLIC.

