

# MasterSeal® SL 1™

One-component elastomeric, self-leveling polyurethane sealant

FORMERLY SONOLASTIC® SL1™

## PACKAGING

- 5 gallon pails (18.9 L)
- 2 gallon pails (7.6 L)
- 825 ml cartridges, 12 cartridges per carton
- 300 ml cartridges, 30 cartridges per carton and 12 cartridges per carton

## COLOR

Limestone and Gray (only available in 825 ml cartridges)

## YIELD

See page 3 for charts

## STORAGE

Store in unopened containers in a cool, clean, dry area. Storing at elevated temperatures will reduce shelf life.

## SHELF LIFE

IN BULK  
 6 months when properly stored

## CARTRIDGES

1 year when properly stored

## VOC CONTENT

29 g/L  
 less water and exempt solvents

## DESCRIPTION

MasterSeal SL 1 is one component, non-priming, self-leveling elastomeric polyurethane designed for expansion joints in concrete floors and decks. Use it where flexibility as well as abrasion and puncture resistance are required.

## PRODUCT HIGHLIGHTS

- Movement capability of  $\pm 35\%$  allows expansion and contraction with joint movement
- Abrasion resistant to provide for longer wearing and durability
- Easy to gun for quick installation
- Variety of types and sizes of packaging to help reduce jobsite waste
- No priming needed on most surfaces, offering excellent adhesion
- Self-leveling, so no tooling needed
- Wide application temperature range makes MasterSeal SL1 suitable for all climates
- Excellent weatherability for long-lasting performance

## APPLICATIONS

- Horizontal
- Interior and exterior
- Expansion joints
- Control joints
- Pavers
- Plaza decks
- Industrial floors
- Driveways/garages
- Sidewalks
- Decks
- Parking structures
- Pitch pans

## SUBSTRATES

- Concrete
- Metal

## HOW TO APPLY

### JOINT PREPARATION

1. The product may be used in sealant joints designed in accordance with SWR Institute's Sealants - The Professional's Guide.
2. In optimal conditions, the depth of the sealant should be  $\frac{1}{2}$  the width of the joint. The sealant joint depth (measured at the center) should always fall between the maximum depth of  $\frac{1}{2}$ " and the minimum depth of  $\frac{1}{4}$ ". Refer to Table 1.
3. In deep joints, the sealant depth must be controlled by closed cell backer rod or soft backer rod. Where the joint depth does not permit the use of backer rod, a bond breaker (polyethylene strip) must be used to prevent three-point bonding.

**Technical Data**

**Composition**

MasterSeal SL 1 is a single-component polyurethane sealant, which cures by reaction with atmospheric moisture.

**Compliances**

- ASTM C 920, Type S, Grade P, Class 35, Use T, M, NT, A and O\*
- Federal Specification TTS- 00230C, Type 1, Class A
- Corps of Engineers CRD-C-541
- Canadian Specification CAN/CGSB 19.13-M87, Classification C-1-40-B-N and C-1-25-B-N, No. 81028
- CFI accepted
- \* Refer to substrates in Where to Use.

**Typical Properties**

PROPERTY	VALUE
<b>Service temperature range,</b> °F (°C)	-40 to 180 (-40 to 82)
<b>Shrinkage</b>	Nil

**Test Data**

PROPERTY	RESULTS	TEST METHOD
<b>Movement Capability, %</b>	±35	ASTM C 719
<b>Tensile strength, psi (MPa)</b>	300 (2.1)	ASTM D 412
<b>Elongation, %</b>	800	ASTM D 412
<b>Hardness, Shore A</b>	25	ASTM C 661
<b>Artificial weathering,</b> Xenon arc, 1,000 hrs	Excellent	ASTM G 26
<b>Low temperature flexibility,</b> °F (°C)	-15 (-26)	ASTM C 793
<b>Viscosity, poise</b>	325	Brookfield

Test results are typical values obtained under laboratory conditions. Reasonable variations can be expected.

TABLE 1

**Joint Width and Sealant Depth**

JOINT WIDTH, IN (MM)	SEALANT DEPTH AT MIDPOINT, IN (MM)
¼–½ (6–13)	¼ (6)
½–¾ (13–19)	¼–⅜ (6–10)
¾–1 (19–25)	⅜–½ (10–13)
1–1½ (25–38)	½ (13)

4. To maintain the recommended sealant depth, install backer rod by compressing and rolling it into the joint channel without stretching it lengthwise. Closed cell backer rod should be about ⅛" (3 mm) larger in diameter than the width of the joint to allow for compression. Soft backer rod should be approximately 25% larger in diameter than the joint width. The sealant does not adhere to it, and no separate bond breaker is required. Do not prime or puncture the backer rod.

**SURFACE PREPARATION**

Substrates must be structurally sound, fully cured, dry and clean. Substrates should always be free of the following: dirt, loose particles, oil, grease, asphalt, tar, paint, wax, rust, waterproofing or curing and parting compounds, membrane materials and sealant residue.

**NEW CONCRETE**

Remove all loose material from joints by wire brushing. Sandblast surfaces in contact with form- release agents. Fresh concrete must be fully cured. Laitance must be removed by abrading.

**OLD CONCRETE**

For previously sealed joints, remove all old material by mechanical means. If joint surfaces have absorbed oils, remove sufficient concrete to ensure a clean surface.

**PRIMING**

1. For most applications, priming is not required; joints subject to periodic water immersion, however, must be primed with MasterSeal P 173. On surfaces other than concrete, conduct a test application to verify adhesion.
2. Apply primer in a thin, uniform film. Avoid buildup of excess primer.
3. Avoid applying primer beyond joint faces. To minimize the contamination of adjacent surfaces, apply masking tape before priming

and remove before the sealant has begun to thicken and set.

4. Allow approximately 15–30 minutes drying time before applying sealant (primer should be tack-free). Priming and sealing must be done on the same day.

**APPLICATION**

1. Fill joints by pouring the sealant from a spouted container.
2. Fill joints from the bottom; avoid bridging of the joint, which may form air voids. Sealant will self-level to form a clean joint surface.

**CURING TIME**

The cure of MasterSeal SL 1 varies with temperature and humidity. The following times assume 75 °F (24 °C), 50% relative humidity, and a joint 1/2" width by ¼" depth (13 by 6 mm).

- Skins: overnight or within 24 hours
- Full cure: approximately 1 week

**Yield**

LINEAR FEET PER GALLON\*

JOINT DEPTH, (INCHES)	JOINT WIDTH (INCHES)									
	1/4	3/8	1/2	5/8	3/4	7/8	1	1 1/2	2	3
1/4	308	205	154	122	–	–	–	–	–	–
3/8	–	–	–	82	68	58	51	–	–	–
1/2	–	–	–	–	51	44	38	26	19	12

METERS PER LITER

JOINT DEPTH, (MM)	JOINT WIDTH (MM)									
	6	10	13	16	19	22	25	38	50	75
6	24.8	16.5	12.4	9.8	–	–	–	–	–	–
10	–	–	–	6.6	5.5	4.7	4.1	–	–	–
13	–	–	–	–	4.1	3.5	3.0	2.2	1.5	0.7

LINEAR FEET PER 825 ML CARTRIDGE

JOINT DEPTH, (INCHES)	JOINT WIDTH (INCHES)							
	1/4	3/8	1/2	5/8	3/4	7/8	1	
1/4	72	48	36	28.5	–	–	–	
3/8	–	–	–	19.25	16	13.5	12	
1/2	–	–	–	–	12	10.2	8.8	

LINEAR METER PER 825 ML CARTRIDGE

JOINT DEPTH, (MM)	JOINT WIDTH (MM)							
	6	10	13	16	19	22	25	
6	20.5	13.6	10.2	8.1	–	–	–	
10	–	–	–	5.4	4.5	3.9	3.4	
13	–	–	–	–	3.4	2.9	2.5	

#### CLEANUP

Clean equipment with MasterSeal 990 or xylene immediately after use and before sealant has cured. Cured sealant may be removed by cutting with a sharp-edged tool, thin films by abrading.

#### FOR BEST PERFORMANCE

- Do not allow uncured MasterSeal SL 1 to come into contact with alcohol-based materials or solvents.
- Do not apply polyurethane sealants in the vicinity of uncured silicone sealants or uncured MasterSeal NP 150™.
- MasterSeal SL 1 is not intended for continuous water immersion. Contact Technical Service for recommendations.
- Backer rods, joint fillers and bond breakers must be tightly installed to prevent loss of sealant through joint bottoms.
- Joints subject to puncture by high heels or umbrella points require a stiffer or higher density backup material; cork or rigid non-impregnated cane-fiber joint fillers are suitable. Separate materials from the sealant by a non-adhering bond breaker (polyethylene tape).
- High temperatures or humidity may cause uncured material to bubble.
- Sealant may bubble if substrates are not dry or if material is applied too deep.
- Do not use other caulks, sand, or incompressibles as a bottom bed in a joint.
- Do not install when rain is expected before the sealant develops a substantial skin.
- For joint widths over 1 1/2" (38 mm), use MasterSeal SL2.
- Proper application is the responsibility of the user. Field visits by Master Builders Solutions personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.

#### HEALTH, SAFETY AND ENVIRONMENTAL

Read, understand and follow all Safety Data Sheets and product label information for this product prior to use. The SDS can be obtained by visiting [www.master-builders-solutions.com/en-us](http://www.master-builders-solutions.com/en-us). Master Builders Solutions.us, e-mailing your request to [mbsbscst@mbcc-group.com](mailto:mbsbscst@mbcc-group.com) or calling 1(800)433-9517. Use only as directed.

**IN CASE OF EMERGENCY: Call CHEMTEL +1 (800) 255-3924 or if outside the US or Canada, +1 (813) 248-0585.**

#### LIMITED WARRANTY NOTICE

Master Builders Solutions Construction Systems US, LLC ("Master Builders") warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. MASTER BUILDERS MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is shipment to purchaser of product equal to the amount of product that fails to meet this warranty or refund of the original purchase price of product that fails to meet this warranty, at the sole option of Master Builders. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. MASTER BUILDERS WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on Master Builders' present knowledge and experience. However, Master Builders assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. Master Builders reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.

**FOR PROFESSIONAL USE ONLY. NOT FOR SALE TO OR USE BY THE GENERAL PUBLIC.**