

MasterTop[®] 1291 GLAZ

Glazed, light-reflective wall coating

FORMERLY SELBAGLAZE[®]

YIELD

Primer: 200 ft²/gallon (5 m²/L)

Topcoat: 250 ft²/gallon (6.25 m²/L)

Final topcoat: 300 ft²/gallon (7.5 m²/L)

All coverage rates are approximate.

Coverage rates will vary with the desired texture and the porosity of the concrete.

PACKAGING

Epoxy Primer and Topcoat:

5 gallon (18.95 L) pails

55 gallon (208 L) drums by special order

Pigments: 1 pint can

Polyurethane and Polyaspartic Topcoats:

5 gallon (18.95 L) pails

COLOR

White

7 standard colors; see the Master Builders Solutions Performance Flooring Color Guide. Custom colors are subject to minimum quantities and increased manufacturing lead-times. Contact Master Builders Solutions for further information.

NOTE: Where color stability is critical, use MasterTop TC 421 UHW or MasterTop TC 693 as a finish coat.

SHELF LIFE

Epoxy primer and topcoat: 2 years

Polyurethane topcoat: 1 year

STORAGE

Store and transport in unopened containers in a clean, dry area.

Protect from freezing.

VOC CONTENT

See MasterTop 1291 GLAZ LEED Letter

See MasterTop GP 500 LEED Letter

DESCRIPTION

MasterTop 1291 GLAZ is a high-solids, glazed epoxy wall system. It is used as a wall and ceiling coating where impact resistance, light reflectivity, and chemical resistance are required.

PRODUCT HIGHLIGHTS

Epoxy technology provides high chemical resistance to a wide range of chemicals

- Tough, durable finish
- Hard, glossy surface that is easy to maintain and clean
- High solids formulation is low in odor and VOC compliant in all regions
- GP500 coatings are 100% solids epoxy polymer systems, very low VOC and universally compliant
- Heavy body coat, handles impact

APPLICATIONS

- Food-preparation and handling areas
- Hospital operating rooms
- Pharmaceutical handling areas
- Clean rooms
- Correctional facilities
- Bathrooms
- Showers
- Animal hospitals

LOCATION

- Vertical surfaces
- Interior

SUBSTRATE

- Over concrete, drywall, plaster, and concrete block

TECHNICAL DATA

COMPOSITION

MasterTop 1291 GLAZ is a high-solids epoxy-polymer system.

TEST DATA

PROPERTY	RESULTS	TEST METHODS
Adhesion , psi (MPa)	350 (2.4)	ASTM C 4541
Abrasion , mg loss	0.087	ASTM D 4060
Moisture-vapor transmission , perms	0.4	ASTM E 96
Impact resistance	No chipping, cracking, or delamination	MIL-D-3134
Rate of burning	Self-extinguishing	ASTM D 635
Hardness , Shore D	85	ASTM D 2240

Unless otherwise noted, test samples were cured 7 days at 73 °F (23 °C) and 50% relative humidity.

CHEMICAL RESISTANCE

For information on resistance to specific chemical reagents, refer to the appropriate Master Builders Solutions Performance Flooring Chemical Resistance test data sheet.

HOW TO APPLY

SURFACE PREPARATION

Surface preparation will depend on the substrate. Surface must be clean, dry and structurally sound. Profile to ICRI CSP 3. Fill all hairline cracks, holes, or other defects and sand smooth. Vertical surfaces must be paint-ready. For more information, contact your Master Builders Solutions representative. Apply a 25 ft² (2.35 m²) test in an inconspicuous area that meet the owner's expectations for appearance and performance.

MIXING

- Mix the components for this product in the following ratios.

TYPICAL PROPERTIES

APPLICATION COMPONENTS	MIX RATIO BY VOLUME
Standard Components MasterTop GP 500 Part A / Part B + optional MasterTop PGM 1000 pigment	2 to 1
Thixotropic MasterTop GP 500 Part A / MasterTop BC 500 TIX Part B	2.5 to 1
Faster Set, ±3 hrs MasterTop GP 500 Part A / MasterTop BC 500FS Part B	2 to 1
Higher Temperature and Chemical Ability MasterTop GP 500 Part A / MasterTop BC 500HT Part B	2 to 1
Topcoat MasterTop TC 504 Part A / MasterTop BC 500TIX Part B	2.5 to 1
Final Topcoat MasterTop TC 421 UHW Part A / Part B MasterTop TC 693 Part A / Part B (Optional Part C)	4 to 1

- Properly mix each component separately before mixing together to ensure uniform consistency.
- Combine Parts A and B in a suitably sized container. Use the proper ratios of A and B; scrape the sides of the containers to ensure a complete reaction.
- Mix properly for 3 minutes with a slow-speed drill and Jiffy-style mixing paddle at 350 rpms. Keep the paddle below the surface to avoid entrapping air. Do not mix by hand.

APPLICATION

- The rendering of a smooth finish may require the use of a foundation coat by spray, roller, or trowel parging.
- Apply the primer coat at 200 ft²/gallon (5 m²/L). Allow to cure
- Apply the topcoat at 250 ft²/gallon (6.25 m²/L). Allow to cure. Additional coats may be required to achieve the desired surface.
- Apply the final topcoat at approximately 300 ft² (7.5 m²/L). Allow to cure 24 hours.

DRYING TIME

Primer: 12 – 24 hours
 Topcoat: 12 – 24 hours
 Topcoat of MasterTop TC 421 UHW or MasterTop TC 693: 24 hours

MAINTENANCE

Regular cleaning and maintenance will prolong the life of all polymer flooring systems, enhance their appearance, and reduce any tendency to retain dirt. Refer to the Master-Top Cleaning and Maintenance Guide for additional information.

FOR BEST PERFORMANCE

- Do not exceed the recommended recoat window of 24 hours. If in doubt, contact your Master Builders Solutions representative or flooring specialist.
- Use MasterTop 421 UHW or MasterTop TC 693 as a finish coat for increased abrasion resistance, color retention, and UV stability.
- Precondition this product to 70 °F (21 °C) for 24 hours before using.
- Do not expose MasterTop 1291 GLAZ to any chemicals until fully cured (7 days).
- Install these products at a substrate temperature of 50 to 85 °F (10 to 30 °C).
- Master Builders Solutions representatives and flooring specialists are available to assist you in the selection of the proper coating system. Call 1-800-243-6739 for in-house and field technical assistance.
- Make certain the most current versions of product data sheet and SDS are being used; call Customer Service (1-800-433-9517) to verify the most current versions.
- Proper application is the responsibility of the user. Field visits by Master Builders Solutions personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.

HEALTH, SAFETY AND ENVIRONMENTAL

Health, Safety and Environmental Read, understand and follow all Safety Data Sheets and product label information for this product prior to use. The SDS can be obtained by visiting www.master-builders-solutions.com/en-us, e-mailing your request to mbsbscst@mbcc-group.com or calling 1(800)433-9517. Use only as directed.

IN CASE OF EMERGENCY: Call CHEMTEL +1 (800) 255-3924 or if outside the US or Canada, +1 (813) 248-0585.

LIMITED WARRANTY NOTICE

Master Builders Solutions Construction Systems US, LLC ("Master Builders") warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. MASTER BUILDERS MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is shipment to purchaser of product equal to the amount of product that fails to meet this warranty or refund of the original purchase price of product that fails to meet this warranty, at the sole option of Master Builders. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. MASTER BUILDERS WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on Master Builders' present knowledge and experience. However, Master Builders assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. Master Builders reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.

FOR PROFESSIONAL USE ONLY. NOT FOR SALE TO OR USE BY THE GENERAL PUBLIC.