



SENERFLEX PLATINUM CI Wall System - Section 072419

Specification for a water-drainage exterior cladding system featuring NEOPOR® GPS PLUS Insulation Board or channeled NEOPOR GPS PLUS Insulation Board, incorporating vertical drainage channels and an air/water-resistive barrier

INTRODUCTION

This specification has been assembled to enable the design professional to select or delete sections to suit the project requirements and is intended to be used in conjunction with Senergy® typical details, product bulletins, technical bulletins, etc.

DESIGN RESPONSIBILITY

It is the responsibility of both the specifier and the purchaser to determine if a product is suitable for its intended use. The designer selected by the purchaser shall be responsible for all decisions pertaining to design, detail, structural capability, attachment details, shop drawings and the like. The Wall Systems business of BASF Corporation (herein referred to as "BASF Wall Systems") has prepared guidelines in the form of specifications, typical application details, and product bulletins to facilitate the design process only. BASF Wall Systems is not liable for any errors or omissions in design, detail, structural capability, attachment details, shop drawings or the like, whether based upon the information provided by BASF Wall Systems or otherwise, or for any changes which the purchasers, specifiers, designers or their appointed representatives may make to BASF Wall Systems published comments.

DESIGNING AND DETAILING A SENERFLEX PLATINUM CI WALL SYSTEM

General: The system shall be installed in strict accordance with current recommended published details and product specifications from the system's manufacturer.

A. Wind Load

1. Maximum deflection not to exceed $L/240$ of span under positive or negative design loads unless otherwise approved in writing by BASF Wall Systems before installation.
2. Design for wind load in conformance with local code requirements.

B. Substrate Systems:

1. Acceptable substrates are: PermaBase Cement Board and other cement-boards conforming with ASTM C1325 (Type A-exterior); poured concrete/unit masonry; ASTM C1177 type sheathings, including, Weather Defense™ Platinum sheathing, GreenGlass sheathing, eXP™ sheathing, GlasRoc sheathing, Securock™ glass-mat sheathing, and DensGlass® exterior sheathing, DensElement (sheathing only); gypsum sheathing (ASTM C79/C1396); Exposure I or exterior plywood (Grade C/D or better); or Exposure I OSB.
2. Painted and otherwise coated surfaces of brick, unit masonry, stucco and concrete shall be inspected and prepared as approved by BASF Wall Systems before application. Other substrates shall be approved by the system's manufacturer in writing prior to the application. The applicator shall verify that the proposed substrate is acceptable prior to the SENERFLEX PLATINUM CI Wall System installation.
3. The substrate systems' structural performance shall be engineered by others.

C. Moisture Control

1. Prevent the accumulation of water, either by condensation or leakage through the wall construction, in the design and detailing of the wall assembly.
 - a. Provide flashing to direct water to the exterior where it is likely to penetrate components in the wall assembly, including, above window and door heads, beneath window and door sills, at roof/wall intersections, decks, abutments of lower walls with higher walls, above projecting features, and at the base of the wall and anywhere else required by local code.
 - b. Air Leakage Prevention: Provide continuity of air barrier system at foundation, roof, windows, doors and other penetrations through the system with connecting and compatible air barrier components to minimize condensation and leakage caused by air movement.

SENERFLEX PLATINUM CI WALL SYSTEM

- c. Vapor Diffusion and Condensation: Perform a dew point analysis of the wall assembly to determine the potential for accumulation of moisture in the wall assembly as a result of water vapor diffusion and condensation. Adjust insulation thickness and/or other wall assembly components accordingly to minimize the risk of condensation. Avoid the use of vapor retarders on the interior side of the wall in warm, humid climates.

D. Impact Resistance

1. Provide ultra-high impact resistance to a minimum height of 6'- 0" (1.8m) above finished grade at all areas accessible to pedestrian traffic and other areas exposed to abnormal stress or potential impact. Indicate the areas with impact resistance requirements other than "Standard" on contract drawings.

E. Color Selection

1. The use of dark colors must be considered in relation to wall surface temperature as a function of local climate conditions. Select Senergy finish color with a light reflectance value (LRV) of 20% or higher. The use of dark colors (LRV less than 20%) is not recommended with NEOPOR GPS PLUS Insulation Board. NEOPOR GPS PLUS Insulation Board has a sustained service temperature limitation of approximately 165°F (74°C).

F. System Joints

1. Expansion joints in the system are required at building expansion joints, at prefabricated panel joints, floor lines of wood frame construction, where substrates change at termination of dissimilar materials and where structural movement is anticipated. It is the sole responsibility of the project design team, including the architect, engineer, etc., to ultimately determine specific expansion joint placement, width and design. Detail specific locations in construction drawings.
2. Sealant joints are required at all penetrations through the SENERFLEX PLATINUM CI (windows, doors, etc.)
3. Specify compatible closed cell backer rod and acceptable sealant which has been evaluated in accordance with ASTM C1382 and meets minimum 50% elongation after conditioning.
4. The system must be properly terminated (back-wrapped a min. of 2" (50 mm), properly sealed, flashed) at all penetrations, lighting fixtures, electrical outlets, hose bibs, dryer vents, etc.

G. Grade Condition

1. SENERFLEX PLATINUM CI is not intended for use below grade or on surfaces subject to continuous or intermittent immersion in water or hydrostatic pressure. Ensure a minimum 8" (203.2 mm) clearance above grade or as required by code, a minimum 1" (25.4 mm) clearance above finished grade (sidewalk/concrete flatwork).

H. Trim, Projecting Architectural Features

(NOTE TO SPECIFIER: Installation of the Senergy Wall System outside the slope guidelines referenced in this specification may still qualify for a standard warranty; however, low sloping conditions are subject to extreme heat, increased maintenance and premature deterioration of the system shall be expected and any deleterious effects caused by the lack of slope will not be the responsibility of BASF Wall Systems. Senergy Wall Systems are designed and tested to be applied to vertical surfaces. The design professional has the option to build according to his/her project needs. The design professional must also consider geography, climate, building orientation, wall orientation and adjacent building components. The slope guidelines referenced below are provided to offer assistance to the owner and/or design professional. Final design of any building is the responsibility of the design professional.)

1. Minimum slope for all projections shall be 1:2 (27°) with a maximum length of 12" (30.5 cm) [e.g. 6" in 12" (15 cm in 30.5 cm)]. Increase slope for northern climates to prevent accumulation of ice/snow on the surface.

I. Coordination with other trades

1. Evaluate adjacent materials such as windows, doors, etc. for conformance to manufacturer's details. Adjacent trades shall provide scaled shop drawings for review.
2. Air seals at any joints/gaps between adjoining components (penetrations, etc.) are of primary importance to maintain continuity of an air barrier system and must be considered by the design professional in the overall wall assembly design. Install air seals between the primary air/water-resistive barrier and other wall components (penetrations, etc.) in order to maintain continuity of an air barrier system.

3. Provide protection of rough openings in accordance with air/water-resistive/vapor barrier application guidelines before installing windows, doors, and other penetrations through the wall.
4. Install copings and sealant immediately after installation of the SENERFLEX PLATINUM CI and when Senergy finishes are completely dry.

TECHNICAL INFORMATION

Consult BASF Wall Systems' Technical Services department for specific recommendations concerning all other applications. Consult the Senergy website, www.senergy.basf.com, for additional information about products and systems and for updated literature.

SENERFLEX PLATINUM CI WALL SYSTEM

PART 1 GENERAL

NOTE TO SPECIFIER: Items in blue/underlined indicate a system option or choice of options. Throughout the specification, delete those which are not required or utilized.

1.01 SECTION INCLUDES

- A. Refer to all drawings and other sections of this specification to determine the type and extent of work therein affecting the work of this section, whether or not such work is specifically mentioned herein.
- B. SENERFLEX PLATINUM CI: Composite wall exterior insulated cladding system consisting of Senergy air/water-resistive barrier, Senergy adhesive, NEOPOR GPS PLUS Rigid Insulation, mechanical fasteners, base coat, reinforcing mesh, and Senergy finish.
- C. Senergy products are listed in this specification to establish a standard of quality. Any substitutions to this specification shall be submitted to and receive approval from the Architect at least 10 days before bidding. Proof of equality shall be borne by the submitter.
- D. The system type shall be SENERFLEX PLATINUM CI as manufactured by the BASF Wall Systems.

1.02 RELATED SECTIONS

- A. Section 03 00 00 Concrete substrate
- B. Section 04 00 00 Masonry substrate
- C. Section 05 40 00 Cold-formed metal framing
- D. Section 06 16 00 Sheathing
- E. Section 06 11 00 Wood framing
- F. Section 07 27 00 Air barriers
- G. Section 07 62 00 Sheet metal flashing and trim
- H. Section 07 65 00 Flexible flashing
- I. Section 07 90 00 Joint protection
- J. Section 08 00 00 Openings
- K. Section 09 22 00 Supports for plaster and gypsum board
- L. Section 09 22 16 Non-structural metal framing
- M. Section 09 29 00 Gypsum board

1.03 DEFINITIONS

Exterior Water Drainage Cladding System: An exterior system comprised of air/water-resistive barrier, adhesive, NEOPOR GPS PLUS Insulation Board, base coat, reinforcing mesh, and finish.

1.04 SUBMITTALS

- A. Submit under provisions of Section [01 33 00]
- B. Product Data: Provide data on SENERFLEX PLATINUM CI materials, product characteristics, performance criteria, limitations and durability.
- C. Code Compliance : Provide manufacturer's applicable code compliance report.
- D. Samples: Submit [two] [x] [millimeter] [inch] size samples of SENERFLEX PLATINUM CI illustrating Senergy finish color and texture range.
- E. Certificate: System manufacturer's approval of applicator.
- F. Sealant: Sealant manufacturer's certificate of compliance with ASTM C1382.
- G. System manufacturer's current specifications, typical details, system design guide and related product literature which indicate preparation required, storage, installation techniques, jointing requirements and finishing techniques.

1.05 QUALITY ASSURANCE

- A. Manufacturer: More than 10 years in the exterior cladding industry, with more than 1000 completed projects.
- B. Applicator: Approved by BASF Wall Systems in performing work of this section.
- C. Regulatory Requirements: Conform to applicable code requirements for exterior cladding system.
- D. Field Samples
 - 1. Provide under provisions of Section [01 43 36] [01 43 39].
 - 2. Construct one field sample panel for each color and texture, [x] [meters] [feet] in size of system materials illustrating method of attachment, surface finish color and texture.
 - 3. Prepare each sample panel using the same tools and techniques to be used for the actual application.
 - 4. Locate sample panel where directed.

5. Accepted sample panel [\[may\]](#) [\[may not\]](#) remain as part of the work.
6. Field samples shall be comprised of all wall assembly components including substrate, air/water-resistive barrier NEOPOR GPS PLUS Insulation Board, base coat, reinforcing mesh, primer (if specified), finish and typical sealant/flashing conditions.

E. Testing:

1. General Air/Water-Resistive Barrier Minimum Performance:

TEST	METHOD	CRITERIA	RESULTS
Water-resistive barrier coatings used under insulated systems	ASTM E2570		Meets all performance requirements
Air Leakage of Air Barrier Assemblies	ASTM E2357	0.2 l/(s.m ²) @75 Pa (0.04 cfm/ft ² @ 1.57 psf)	0.0007 l/s.m ² (0.0001 cfm/ft ²) @ 75 Pa (1.57 psf) positive / post conditioning 0.0014 l/s.m ² (0.0003 cfm/ft ²) @ 75 Pa (1.57 psf) negative / post conditioning
Air Permeance of Building Materials	ASTM E2178	0.02 l/(s.m ²) @75 Pa (0.004 cfm/ft ² @ 1.57 psf)	0.0049 l/s.m ² @ 75 Pa (0.00098 cfm/ft ² @ 1.57 psf)
Rate of Air Leakage	ASTM E283		0.0185 l/s.m ² @ 75 Pa (0.0037 cfm/ft ² @ 1.57 psf)
Water Vapor Transmission	ASTM E96	Report value	Senersshield-R - 18 Perms (grains/Hr. in Hg. ft ²) @ 10 mils wet film thickness Senersshield-R - 14 Perms (grains/Hr. in Hg. ft ²) @ 20 mils wet film thickness Senersshield-RS - 18 Perms (grains/Hr. in Hg. ft ²) @ 10 mils wet film thickness Senersshield-RS - 14 Perms (grains/Hr. in Hg. ft ²) @ 20 mils wet film thickness Senersshield-VB - 0.09 Perms (grains/Hr. in Hg. ft ²) @ 26 mils wet film thickness
Pull-Off Strength of Coatings	ASTM D4541	Min. 110 kPa (15.9 psi) or substrate failure	Pass - Tested over exterior gypsum sheathing, ASTM C1177 glass-mat sheathing, cement board, OSB, plywood; PVC and galvanized flashing
Nail Sealability (without BASF SHEATHING FABRIC)	ASTM D1970	No water penetration at galvanized roofing nail penetration under 127 mm (5") head of water after 3 days at 4° C (40° F)	Pass
Surface Burning	ASTM E84	Flame Spread < 25 Smoke Development < 450	Meets Class A: Flame spread =15 Smoke developed = 95

2. Air/Water-Resistive Barrier ICC-ES AC-212:

TEST	METHOD	CRITERIA	RESULTS
Sequential Testing: 1. Structural 2. Racking 3. Restrained Environmental Conditioning 4. Water Penetration	1. ASTM E 1233 Procedure A 2. ASTM E 72 3. ICC-ES AC-212 4. ASTM E 331	No cracking at joints or interface of flashing No water penetration after 15 min @ 137 Pa (2.86 psf)	Pass - Tested over OSB and gypsum sheathing No water penetration after 90 min @ 299 Pa (6.24 psf)
Sequential Testing: 1. UV Light Exposure 2. Accelerated Aging 3. Hydrostatic Pressure Test	1. ICC-ES AC-212 2. ICC-ES AC-212 3. AATCC 127-1985	No cracking or bond failure to substrate No water penetration after 21.7 in (550 mm) water for 5 hours	Pass
Freeze-Thaw	ASTM E 2485 (Method B)	No sign of deleterious effects after 10 cycles	Pass - Tested over exterior gypsum sheathing, ASTM C1177 glass-mat sheathing, cement board, OSB, plywood
Water Resistance	ASTM D2247	No deleterious effects after 14 day exposure	Pass - Tested over exterior gypsum sheathing, ASTM C1177 glass-mat sheathing, cement board, OSB, plywood
Tensile Bond	ASTM C 297	Minimum 103 kPa (15 psi)	Pass - Tested over exterior gypsum sheathing, ASTM C1177 glass-mat sheathing, cement board, OSB, plywood, CMU; PVC and galvanized flashing
Tensile Bond (after freeze-thaw)	ASTM C 297	Minimum 103 kPa (15 psi) avg; no failure after 10 cycles freeze-thaw	Pass

3. Air/Water-Resistance Barrier ICC-ES AC 148:

TEST	METHOD	CRITERIA	RESULTS
------	--------	----------	---------

SENERFLEX PLATINUM CI WALL SYSTEM

Sequential Testing: 1. UV Light Exposure 2. Accelerated Aging 3. Hydrostatic Pressure Test	1. ICC-ES AC 148 2. ICC-ES AC 148 3. AATCC 127-1985	No cracking or bond failure to substrate No water penetration after 21.7 in (550 mm) water for 5 hours	Pass
Peel Adhesion	ASTM D 3330 Method F	After UV Exposure After Accelerated Aging After Elevated Temperature Exposure After Water Immersion	Pass - tested over ASTM C1177 glass-mat sheathing, OSB, plywood, PVC and uncoated aluminum
Nail Sealability after Thermal Cycling	ASTM D 1970 (Modified), AAMA 711	No water penetration at galvanized roofing nail penetration under 31 mm (1.2") head of water after 24 hours at 4° C (40° F)	Pass
Tensile Strength after UV Exposure	ASTM D 5034, AAMA 711	Minimum 0.5 N/mm (2.9 lbs/in)	Pass
Cold Temperature Pliability	ASTM D 1970, AAMA 711	No cracking after bending around a 25 mm (1") mandrel after 2 hour exposure to -18° C (0° F)	Pass
Resistance to Peeling	AAMA 711	No signs of distress or failure after 24 hours of exposure at room temperature, 50° C (122° F), 65° C (149° F), 80° C (176° F)	Pass

4. SENERFLEX PLATINUM CI System and Components Performance:

TEST	METHOD	CRITERIA	RESULTS
EIFS and EIFS with Drainage	ASTM E2568 and ICC-ES AC 235		Meets all performance requirements
Drainage Efficiency	ASTM E2273	90% Minimum	98.7% - Senersshield-R, -RS & Senersshield-VB
Transverse Wind-load	ASTM E330	Steel stud framing (20 gauge) 16"o.c., 1/2" gypsum sheathing, 4" SHEATHING FABRIC over sheathing joints, SENERSHIELD-R, Senergy Adhesive, 1" NEOPOR GPS PLUS Insulation Board, Senergy Base Coat, FLEXGUARD 4 REINFORCING MESH, Senergy Finish.	Average ultimate loads ¹ : - 3126 Pa (- 65 psf) + 2633 Pa (+ 55 psf) not taken to failure
Transverse Wind-load	ASTM E330	Wood assembly (2' x 4') 16"o.c., 7/16" Exposure 1 OSB, 4" SHEATHING FABRIC over sheathing joints, SENERSHIELD-R, Senergy Adhesive, 1" NEOPOR GPS PLUS Insulation Board, Senergy Base Coat, FLEXGUARD 4 REINFORCING MESH, Senergy Finish.	Average ultimate loads ¹ : - 8379 Pa (- 175 psf) + 3591 Pa (+ 75 psf) not taken to failure
Tensile Bond	ASTM C297/E2134	Minimum 103 kPa (15 psi)	Pass
Water Penetration	ASTM E 331	No water penetration after 15 minutes @ 137 Pa (2.86 psf)	Pass
Radiant Heat Exposure	NFPA 268	No ignition at 20 minutes	Met test criteria with 12" thick NEOPOR GPS PLUS insulation.
Fire Endurance	ASTM E119	Maintain fire resistance of existing rated assembly	1-hour rating with maximum 4" thick NEOPOR GPS PLUS insulation
Intermediate Scale Multi-story Fire Test	NFPA 285 / UBC Standard 26-9	1. Resist flame propagation over the exterior surface 2. Resist vertical spread of flame within combustible core/component of panel from one story to the next 3. Resist vertical spread of flame over the interior surface from one story to the next 4. Resist lateral spread of flame from the compartment of fire origin to adjacent spaces	Met test criteria with 12" thick NEOPOR GPS PLUS insulation.
Surface Burning	ASTM E84 / UL 723	Flame spread < 25 Smoke developed < 450	All components of the system meet Class A performance (FS < 25; SD < 450)
Abrasion Resistance	ASTM D968	No cracking or loss of film integrity at 528 qt. (500L) of sand	Finish coat not worn through after 686 liters of falling sand

Accelerated Weathering	ASTM G 153 (formerly G23)	No deleterious effects after 2000 hours.	Pass
Accelerated Weathering	ASTM G 154 (formerly G53)	No deleterious effects after 2000 hours.	Pass - No deleterious effects after 7500 hours.
Freeze-Thaw	ASTM C67, E2485 Method A	No deleterious effects after 60 cycles	Pass
Mildew Resistance	Mil Std 810B Method 508	No fungus growth after 28 days	Pass
Salt Fog Resistance	ASTM B117	No deleterious effects after 300 hours	Pass
Water Resistance of Coating in 100% R.H.	ASTM D 2247	No deleterious effects after 14 days exposure	Pass

¹ No failure in the Senerflex materials; failure in framing and/or sheathing connections

5. Reinforcing Mesh Testing and Impact Resistance

TEST	METHOD	CRITERIA	RESULTS
Alkali Resistance of Reinforcing Mesh	ASTM E 2098	Greater than 120 pli (21 dN/CM) retained tensile strength	Pass (all mesh)
Date County Impact Test	Protocol 201	Large & Small Missile	Passed with various wall assemblies
FLEXGUARD 4	ASTM E2486 (formerly EIMA 101.86)	25-49 inch-lbs. (2.8-5.6 j)	Pass
INTERMEDIATE 6	ASTM E2486 (formerly EIMA 101.86)	25-49 inch-lbs. (2.8-5.6 j)	Pass
INTERMEDIATE 12	ASTM E2486 (formerly EIMA 101.86)	50-89 inch-lbs. (5.7-10.1 j)	Pass
INTERMEDIATE 12 & FLEXGUARD 4	ASTM E2486 (formerly EIMA 101.86)	90-150 inch-lbs. (10.2-17.0 j)	Pass
STRONG 15 & FLEXGUARD 4	ASTM E2486 (formerly EIMA 101.86)	150 inch-lbs. (17 j)	Pass
HI-IMPACT 20 & FLEXGUARD 4	ASTM E2486 (formerly EIMA 101.86)	150 inch-lbs. (17 j)	Pass

1.06 DELIVERY, STORAGE AND HANDLING

- A. Deliver, store and handle products under provisions of Section [01 65 00] [01 66 00] [] .
- B. Deliver SENERFLEX PLATINUM CI materials in original unopened packages with manufacturer's labels intact.
- C. Protect SENERFLEX PLATINUM CI materials during transportation and installation to avoid physical damage.
- D. Store SENERFLEX PLATINUM CI materials in cool, dry place protected from freezing. Store at no less than 40°F/4°C (50°F/10°C for BASF AURORA STONE and BASF AURORA TC-100, BASF ALUMINA Finish).
- E. Store BASF MAXFLASH at a minimum of 40°F/4°C. In cold weather, keep containers at room temperature for at least 24 hours before using.
- F. Store NEOPOR GPS PLUS Insulation Board flat and protected from direct sunlight and extreme heat in original packaging.
- G. Store SENERFLEX PLATINUM CI Reinforcing Mesh, BASF SHEATHING FABRIC and BASF WS FLASH flexible flashing in cool, dry place protected from exposure to moisture.

1.07 PROJECT/SITE CONDITIONS

- A. Do not apply SENERFLEX PLATINUM CI materials in ambient temperatures below 40°F/4°C (50°F/10°C for BASF AURORA STONE, BASF AURORA TC-100 and BASF ALUMINA finish). Provide properly vented, supplementary heat during installation and drying period when temperatures less than 4°C/40°F (50°F/10°C for BASF AURORA STONE, BASF AURORA TC-100 and BASF ALUMINA finish) prevail.
- B. Do not apply SENERFLEX PLATINUM CI materials to frozen surfaces.
- C. Maintain ambient temperature at or above 40°F/4°C (50°F/10°C for BASF AURORA STONE, BASF AURORA TC-100 and BASF ALUMINA Finish) during and at least 24 hours after SENERFLEX PLATINUM CI installation and until dry.

SENERFLEX PLATINUM CI WALL SYSTEM

1.08 SEQUENCING AND SCHEDULING

- A. Coordinate and schedule installation of SENEFLEX PLATINUM CI with related work of other sections.
- B. Coordinate and schedule installation of trim, flashing, and joint sealers to prevent water infiltration behind the system.

1.09 WARRANTY

- A. Provide BASF Wall Systems ten-year limited labor, materials and drainage warranty for SENEFLEX PLATINUM CI installations under provisions of Section [01 70 00]. Reference Senergy's *EIFS, Coatings, and Air/Water-Resistive Barriers Warranty Schedule* technical bulletin for specific information.
- B. Comply with BASF Wall Systems notification procedures to assure qualification for warranty.

PART 2 - PRODUCTS

2.01 MANUFACTURERS

- A. SENEFLEX PLATINUM CI manufactured by BASF Wall Systems.

2.02 MATERIALS

NOTE TO SPECIFIER: Items in blue/underlined indicate a system option or choice of options. Throughout the specification, delete those which are not required or utilized. Contact BASF Wall Systems Technical Service Department for further assistance.

A. Senergy Air/Water-Resistive Barrier Components:

1. Air/Water-Resistive Barrier: **(Required, Select a, b or c)**
 - a. SENERSHIELD-R: A one-component fluid-applied vapor permeable air/water-resistive barrier applied with an airless sprayer.
 - b. SENERSHIELD-RS: A one-component fluid-applied vapor permeable air/water-resistive barrier.
 - c. SENERSHIELD-VB: A one-component fluid-applied vapor impermeable air/water-resistive barrier.
2. Rough Opening and Joint Treatment: **(Required, Select a or b)**
 - a. BASF SHEATHING FABRIC: A spun-bonded non-woven reinforced polyester web for use with Senergy fluid applied air/weather-resistive barriers.
 - b. BASF MAXFLASH: A one-component elastomeric material for use as a flexible flashing membrane.
3. Transitional Membrane / Expansion Joint Flashing (If selected, both a & b are required)
 - a. BASF WS FLASH: 30-mil thick, self-sealing composite membrane of polyester fabric and rubberized asphalt. Compatible with Senergy liquid air/weather resistive barriers.
 - b. BASF FLASHING PRIMER: A water-based primer for use prior to application of BASF WS FLASH on all acceptable surfaces.
4. Cold Temperature Additive:
 - a. LT ADDITIVE: Blending of LT ADDITIVE with a pail of SENERSHIELD-R, SENERSHIELD-RS or SENERSHIELD-VB enables application of these materials at temperatures as low as 25°F (-4°C).

B. Senergy Adhesives/Base Coats: **(Required, Select One or More)**

1. ALPHA Base Coat: A 100% acrylic base coat, field-mixed with Type I or Type II Portland cement. It has a creamy texture that is easily spread.
2. ALPHA DRY Base Coat: A dry-mix polymer adhesive and base coat containing Portland cement, and requiring only water for mixing.
3. XTRA-STOP Base Coat: A 100% acrylic-based, water-resistant base coat, field-mixed with Type I or Type II Portland cement.
4. ALPHA GENIE Base Coat: A 100% acrylic, fiber-reinforced base coat, adhesive and leveler that is field-mixed with Type I or Type II Portland cement.

NOTE TO SPECIFIER: Portland cement is not required if ALPHA DRY Base Coat is specified.

C. Portland cement:

1. Conform to ASTM C150, Type I, II, or I/II, grey or white; fresh and free of lumps.

D. Water:

1. Clean and potable without foreign matter.

E. **Fastener System:** NEOPOR GPS PLUS Insulation Board requires supplemental fasteners installed

immediately after the board is adhesively attached and prior to the drying of the adhesive base coat.
(Required, Select One or More)

1. NEOPOR GPS PLUS Insulation Board: Wind-Devil 2 Mechanical Fastening System manufactured by Wind-lock Corp.
 - a. [Light gauge steel framing \(20 gauge\): Type WLMT or GWLMT fastener and plate system; 5/8" \(16 mm\) minimum penetration into framing.](#)
 - b. [Heavy gauge steel framing \(20 to 12 gauge maximum\): Type ST fastener and plate system; 5/8" \(16 mm\) minimum penetration into framing.](#)
 - c. [Masonry or concrete: Type MT or MET fastener and plate system; 1" \(25 mm\) minimum penetration into masonry or concrete.](#)
 - d. [Wood Framing: Type WLMT, GWLMT or GWT fastener and plate system; 5/8" \(16 mm\) minimum penetration into framing.](#)

F. Insulation Board:

1. NEOPOR GPS PLUS Insulation Board: Thermal resistance values R5, R 7.5, R10 or custom and shapes as specified.
 - a. Flame spread and smoke development 25 and 450 or less respectively per ASTM E84, minimum 25 psi flexural, minimum 10 psi compressive, minimum thermal resistance R5/ 1 1/16" at 75° F (40° C).
 - b. Meets or exceeds ASTM C578 Type I.
 - c. Minimum density 1.0 pcf.
 - d. Aging: For air dry method, store in a minimum ambient temperature of 68° F for a period of six (6) weeks prior to cutting. Mechanical aging shall be at a temperature of 140° F for a period of five (5) days.
 - e. Maximum size 2' x 4' (61 cm x 1.22 m).
 - f. Tolerances: Edges square within 1/32"/ft. (0.8mm/0.3m), width 24" (+/-) 1/16" (61cm (+/-) 1.6mm) and length 48" (+/-) 1/8" (1.22m (+/-) 3mm).
 - g. [Channeled NEOPOR GPS PLUS Insulation Board: ¼" \(6.4mm\) deep, 1" \(25mm\) wide channels 12" \(305mm\) on center parallel to the 2 ft. \(61cm\) dimension on the back surface of the insulation board.](#)

G. Senergy Reinforcing Mesh: Balanced, open-weave glass, fiber reinforcing mesh, twisted multi-end strands treated for compatibility with Senergy Base Coats. **(Required, Select One or More)**

1. [FLEXGUARD 4: Standard weight, 4 oz.](#)
2. [INTERMEDIATE 6: Standard/medium weight, 6 oz.](#)
3. [INTERMEDIATE 12: Intermediate weight, 12 oz.](#)
4. [STRONG 15: Heavy weight, 15 oz. used only in combination with FLEXGUARD 4 or INTERMEDIATE 6.](#)
5. [HI-IMPACT 20: Heavy weight, 20 oz. used only in combination with FLEXGUARD 4 or INTERMEDIATE 6.](#)
6. [BASF CORNER MESH: Intermediate weight, pre-marked for easy bending, for reinforcing at exterior corners.](#)

H. BASF Coating: (Optional)

1. [BASF COLOR COAT: A 100% acrylic-based coating. It is designed for spray-, roller- or brush-application with minimum change in finish texture or sheen.](#)

I. BASF Primer: (Optional)

1. [BASF TINTED PRIMER: A 100% acrylic-based primer that helps alleviate shadowing and enhances performance of the Senergy Wall Systems. Color to closely match the selected Senergy Finish Coat color.](#)

J. Senergy Finish Coat: (Required, Select One or More Finishes and Textures)

1. [SENERFLEX Finish: 100% acrylic polymer finishes with advanced technology to improve long-term performance and dirt pick-up resistance; air cured, compatible with base coat; Senergy finish color \[\] as selected; finish texture:](#)
 - a. [CLASSIC: A finish with a medium "worm-holed" appearance which is achieved by the random aggregate sizes in the Finish. The "worm-holed" look can be circular, random, vertical or horizontal.](#)
 - b. [FINE: A finish which utilizes uniformly-sized aggregates for a uniform, fine texture.](#)
 - c. [TEXTURE: A finish which can achieve a wide variety of free-formed, textured appearances, including stipple and skip-trowel](#)
 - d. [SAHARA: A finish with a uniform, "pebble" appearance.](#)

SENERFLEX PLATINUM CI WALL SYSTEM

2. SENERFLEX TERSUS Finish: A modified acrylic based finish with water repellent properties, compatible with base coat; Senergy Finish color [] as selected; finish texture:
 - a. F1.0: A 1.0 mm uniform aggregate creating a fine texture.
 - b. M1.5: A 1.5 mm uniform aggregate creating a medium sand texture.
3. Specialty Finishes: 100% acrylic polymer finishes that can be hand-troweled to simulate stone or create a time-honored, mottled tone-on-tone look that achieves a soft and weathered patina over time.
 - a. BASF ENCAUSTO VERONA: A finish which utilizes uniformly-sized aggregate to achieve a free-formed, flat texture. It can be used to achieve a mottled look and unlimited tone on tone designs by combining multiple colors.
 - b. BASF METALLIC: A specialty finish which has a pearlescent appearance. It utilizes uniformly-sized aggregates for a uniform fine texture.
 - c. BASF AURORA TC-100: A finish which provides a stone-like appearance, either rough or smooth depending upon application.
 - d. BASF AURORA STONE: A finish which provides a rough, stone-like appearance.
 - e. BASF ALUMINA: A factory-mixed, reflective stone finish consisting of colored aggregate and large black mica flakes in a 100% acrylic transparent binder that provides a classic granite or marble-like textured finished appearance.
4. BASF CHROMA Finish: A 100% acrylic polymer based finish with integrated high performance colorants for superior fade resistance, compatible with base coat; Senergy Finish color [] as selected; finish texture:
 - a. F1.0: A finish which utilizes uniformly-sized aggregates for a uniformly fine texture.
 - b. M1.5: A finish which provides a uniform "pebble" appearance.
 - c. R1.5: A finish which has a medium "worm-holed" appearance which is achieved by the random aggregate sizes in the finish. The "worm-holed" look can be circular, random, vertical or horizontal

K. BASF Glaze/Stain: (Optional)

1. BASF ANTICOGLAZE: 100% acrylic antiquing stain product used to impart an 'old world' mottled look to textured finishes.

PART 3 - EXECUTION

3.01 EXAMINATION

A. Site Conditions:

Verify project site conditions under provisions of Section [01 00 00].

B. Walls:

1. Substrates:
 - a. Acceptable substrates are: PermaBase® Cement Board and other cement-boards conforming with ASTM C1325 (Type A-exterior); poured concrete/unit masonry; ASTM C1177 type sheathings, including, Weather Defense™ Platinum sheathing, GreenGlass® sheathing, eXP™ sheathing, GlasRoc® sheathing, Securock™ glass-mat sheathing, and DensGlass® exterior sheathing. DensElement (sheathing only); gypsum sheathing (ASTM C79/C1396); Exposure I or exterior plywood (Grade C/D or better); or Exposure I OSB. Consult the BASF Wall Systems Technical Services department for all other applications.
 - b. Wall sheathing must be securely fastened per applicable building code and sheathing manufacturer's requirements.
 - c. Examine surfaces to receive SENERFLEX PLATINUM CI and verify that substrate and adjacent materials are dry, clean, sound, and free of releasing agents, paint, or other residue or coatings. Verify substrate is flat, free of fins or planar irregularities greater than 1/4" in 10' (6.4 mm in 3 m).
2. Flashings:
 - a. All flashings are by others and must be installed in accordance with specific manufacturer's requirements. Where appropriate, end-dams must be provided.
 - b. Openings must be flashed prior to window/door, HVAC, etc. installation. Refer to Senergy's *Air/Water-Resistive/Vapor Barrier Application Guidelines* technical bulletin for further information.
 - c. Windows and openings shall be flashed according to design and building code requirements.
 - d. Individual windows that are ganged to make multiple units require continuous head flashing and the joints between the units must be fully sealed.
3. Roof:

Verify that all roof flashings have been installed in accordance with the guidelines set by the Asphalt Roofing Manufacturers Association (ARMA).

4. Kick-out Flashing:

Kick-out flashing must be installed leak-proof and angled (min 100°) to allow for proper drainage and water diversion.

C. Do not proceed until all unsatisfactory conditions have been corrected.

3.02 PREPARATION

A. Protect all surrounding areas and surfaces from damage and staining during application of SENERFLEX PLATINUM CI materials.

B. Protect finished work at end of each day to prevent water penetration.

C. Substrate preparation: Prepare substrates in accordance with Senergy instructions.

3.03 MIXING

General: No additives are permitted unless specified in product mixing instructions. Close containers when not in use. Prepare in a container that is clean and free of foreign substances. Do not use a container which has contained or been cleaned with a petroleum-based product. Clean tools and equipment with water immediately after use. Dried material can only be removed mechanically.

NOTE TO SPECIFIER: Keep only the products in this section which were selected in Section 2.02. Delete those not to be utilized.

A. Senergy Air/Water-Resistive Barriers:

1. SENERSHIELD-R, SENERSHIELD-RS and SENERSHIELD-VB: Mix with a clean, rust-free paddle and drill until thoroughly blended. Do not add water.
2. Cold Temperature Additive: LT ADDITIVE: Pour the entire contents of one (1) bottle of LT ADDITIVE into one (1) full pail of SENERSHIELD-R, SENERSHIELD-RS, or SENERSHIELD-VB. Mix with a clean, rust-free paddle and drill until fully blended.

B. Senergy Base Coat:

1. ALPHA Base Coat: Mix base coat with a clean, rust-free paddle and drill until thoroughly blended, before adding Portland cement. Mix one part (by weight) Portland cement with one-part base coat. Add Portland cement in small increments, mixing until thoroughly blended after each additional increment. Clean, potable water may be added to adjust workability.
2. XTRA-STOP Base Coat: Mix base coat with a clean, rust-free paddle and drill until thoroughly blended, before adding Portland cement. Mix one part (by weight) Portland cement with one-part base coat. Add Portland cement in small increments, mixing until thoroughly blended after each additional increment. Clean, potable water may be added to adjust workability.
3. ALPHA GENIE Base Coat: Mix base coat with a clean, rust-free paddle and drill until thoroughly blended, before adding Portland cement. Mix one part (by weight) Portland cement with one part base coat. Add Portland cement in small increments, mixing until thoroughly blended after each additional increment. Clean, potable water may be added to adjust workability.
4. ALPHA DRY Base Coat: Mix and prepare each bag in a 5-gallon (19-liter) pail. Fill the container with approximately 1.5-gallons (5.6-liters) of clean, potable water. Add ALPHA DRY Base Coat in small increments, mixing after each additional increment. Mix ALPHA DRY Base Coat and water with a clean, rust-free paddle and drill until thoroughly blended. Additional ALPHA DRY Base Coat or water may be added to adjust workability.

C. BASF Coating:

1. BASF COLOR COAT: Mix the factory-prepared material with a clean, rust-free paddle and drill until thoroughly blended. A small amount of clean, potable water may be added to adjust workability. Do not overwater.

D. BASF Primer:

2. BASF TINTED PRIMER: Mix the factory-prepared material with a clean, rust-free paddle and drill until thoroughly blended. A small amount of clean, potable water may be added to adjust workability. Do not overwater.

E. Senergy Finishes:

3. SENERFLEX, SENERFLEX TERSUS, BASF CHROMA, and BASF ENCAUSTO VERONA Finish: Mix the factory-prepared material with a clean, rust-free paddle and drill until thoroughly blended. A small amount of clean, potable water may be added to adjust workability. Do not overwater.

F. BASF Specialty Finishes:

SENERFLEX PLATINUM CI WALL SYSTEM

4. BASF AURORA TC-100, BASF AURORA STONE, and BASF ALUMINA Finish: Gently mix the contents of the pail for 1 minute using a low RPM ½" drill equipped with a mixing paddle such as a Demand Twister or a Wind-lock B-MEW, B-M1 or B-M9.

G. BASF Glaze/Stain:

5. BASF ANTICOGLAZE: mix the contents of the pail with a slow speed drill and paddle mixer until thoroughly blended.

3.04 APPLICATION

NOTE TO SPECIFIER: Keep only the products in this section which were selected in Section 2.02. Delete those not to be utilized.

A. Senergy Air/Water-Resistive Barrier:

1. All sheathing joints and windows/openings must be protected and the air/water-resistive barrier applied in accordance with *Air/Water-Resistive/Vapor Barrier Application Guidelines* technical bulletin.
2. Substrate shall be dry, clean, sound, and free of releasing agents, paint, or other residue or coatings. Verify substrate is flat, free of fins or planar irregularities greater than ¼" in 10' (6.4 mm in 3 m).
3. Unsatisfactory conditions shall be corrected before application of the Senergy air/water-resistive barriers.
4. Apply the BASF SHEATHING FABRIC and Senergy air/water-resistive barrier in accordance with the Senergy air/water-resistive barrier product bulletin.
5. Apply BASF MAXFLASH in accordance with BASF MAXFLASH product bulletin.
6. Installed materials shall be checked before continuing system application.
7. Ensure BASF Sheathing Fabric embedded in Senergy air/water-resistive barrier or BASF MAXFLASH is utilized for transitions to flashing and window flanges or others areas where appropriate. Reference typical details.

B. NEOPOR GPS PLUS Insulation Board:

1. Vertical surfaces: Begin at base of wall with firm, temporary support or spacer.
2. Stagger joints horizontally in a running bond pattern offset a minimum of 6".
3. Pre-cut insulation board to fit openings and projections. Insulation board must be a single piece around corners of openings. Stagger vertical joints and corners. Stagger insulation and sheathing board joints. Offset insulation board joints from sheathing joints by a minimum of 16".
4. Apply mixed Senergy Base Coat to entire surface of insulation board using a stainless steel trowel with 1/2"x 1/2" (13 mm x 13 mm) notches spaced 2" (50 mm) apart. Ribbons of adhesive must be applied parallel to the 2' dimension of the NEOPOR GPS PLUS Insulation Board to ensure they are vertical when the NEOPOR GPS PLUS Insulation Board is applied to the substrate.
5. Immediately set board into place and apply pressure over entire surface of board to ensure positive uniform contact and high initial grab. Do not slide board into place. Do not allow base coat to dry prior to installing.
6. Abut all joints tightly and ensure overall flush level surface.
7. Fill 1/16" and larger gaps between insulation boards with slivers of insulation board.
8. Check adhesion periodically by removing a board prior to set. Properly installed insulation board will be difficult to remove and Senergy Adhesive/Base Coat will be adhered to both the Senergy Air/Water-Resistive Barrier and the insulation board.
9. Allow application of insulation board to dry (normally 8 to 10 hours) prior to application of base coat/reinforcing mesh.
10. Rasp flush any irregularities of the insulation board greater than 1/16" 1.6 mm).
11. Install expansion joints and aesthetic grooves as indicated on drawings. Do not align aesthetic grooves with insulation board joints.

C. Mechanical Fastening of Insulation Board:

1. NEOPOR GPS PLUS Insulation Board requires supplemental fasteners installed immediately after the board is adhesively attached and prior to the drying of the adhesive base coat. See *Platinum CI Neopor GPS Plus Supplemental Fasteners* technical bulletin for fastener patterns.
 - a. Light gauge steel framing (20 gauge): Type WLMT or GWLMT fastener and plate system; 5/8" (16 mm) minimum penetration into framing.
 - b. Heavy gauge steel framing (20 to 12 gauge maximum): Type ST fastener and plate system; 5/8"

- (16 mm) minimum penetration into framing.
- c. Masonry or concrete: Type MT or MET fastener and plate system; 1" (25 mm) minimum penetration into masonry or concrete.
 - d. Wood Framing: Type WLMT, GWLMT or GWT fastener and plate system; 5/8" (16 mm) minimum penetration into framing.

D. Senergy Base Coat/Reinforcing Mesh:

1. Base coat shall be applied to achieve reinforcing mesh embedment with no reinforcing mesh color visible.

NOTE TO SPECIFIER: Indicate on drawings the required locations of standard, medium, high or ultra-high impact reinforcing mesh.

E. BASF CORNER MESH:

1. Install BASF CORNER MESH at corners.
2. Apply BASF CORNER MESH prior to application of reinforcing mesh.
3. Cut BASF CORNER MESH to workable lengths.
4. Apply mixed Senergy Base Coat to insulation board at outside corners using a stainless steel trowel.
5. Immediately place BASF CORNER MESH against the wet base coat and embed the BASF CORNER MESH into the base coat by troweling from the corner; butt edges and avoid wrinkles.
6. After base coat is dry and hard, apply a layer of FLEXGUARD 4, INTERMEDIATE 6 or 12 Reinforcing Mesh over the entire surface of the BASF CORNER MESH in accordance with 3.04 F.

F. Standard Impact or Medium Impact Resistance Reinforcing Mesh: FLEXGUARD 4

INTERMEDIATE 6 and INTERMEDIATE 12

1. Install Senergy Reinforcing Mesh where indicated on drawings.
2. Apply mixed Senergy Base Coat to entire surface of insulation board with a stainless steel trowel to embed the reinforcing mesh.
3. Immediately place Senergy Reinforcing Mesh against wet base coat and embed the reinforcing mesh into the base coat by troweling from the center to the edges.
4. Lap reinforcing mesh 2 ½" (64 mm) minimum at edges.
5. Ensure reinforcing mesh is continuous at corners, void of wrinkles and embedded in base coat so that no reinforcing mesh color is visible.
6. If required, apply a second layer of base coat to achieve total nominal base coat/reinforcing mesh thickness of 1/16" (1.6 mm).
7. Allow base coat with embedded reinforcing mesh to dry hard (normally 8 to 10 hours).

G. High Impact or Ultra High Impact Resistance Reinforcing Mesh: INTERMEDIATE 12, STRONG 15 and HI-IMPACT 20

NOTE TO SPECIFIER: Where STRONG 15 or HI-IMPACT 20 is specified, FLEXGUARD 4 or INTERMEDIATE 6 must be specified also.

1. Install Senergy Reinforcing Mesh where indicated on drawings.
2. Apply mixed Senergy Base Coat to entire surface of insulation board with a stainless steel trowel to embed the reinforcing mesh.
3. Immediately place Senergy Reinforcing Mesh against wet base coat and embed the reinforcing mesh into the base coat by troweling from the center to the edges.
4. Butt Senergy Reinforcing Mesh at all adjoining edges; do not use to backwrap or bend around corners.
5. Butt Senergy Reinforcing Mesh at adjoining edges of BASF CORNER MESH.
6. Ensure reinforcing mesh is free of wrinkles and embedded in base coat so that no reinforcing mesh color is visible.
7. After base coat with embedded reinforcing mesh is dry and hard (normally 8 to 10 hours), apply a layer of FLEXGUARD 4 or INTERMEDIATE 6 Reinforcing Mesh over the entire surface in accordance with 3.04 F to achieve total nominal base coat/ reinforcing mesh thickness of 3/32" (2.4 mm).

H. BASF COLOR COAT:

1. Apply material to the base coat/reinforcing mesh in sealant joints with a high-quality, latex-type paintbrush.
2. Work material continuously until a uniform appearance is obtained.
3. Allow to dry thoroughly (approximately 24 hours) prior to application of sealant primer and sealant.

I. BASF TINTED PRIMER:

SENERFLEX PLATINUM CI WALL SYSTEM

1. Apply BASF TINTED PRIMER to the base coat/reinforcing mesh with a sprayer, 10 mm ($\frac{3}{8}$ ") nap roller, or good quality latex paint brush at a rate of approximately 150-250 ft² per gallon (3.6–6.1m² per liter).
2. BASF TINTED PRIMER shall be dry to the touch before proceeding to the Senergy Finish coat application.

J. Senergy Finish Coat: SENERFLEX, SENERFLEX TERSUS and BASF CHROMA.

1. Apply Senergy Finish directly to the base coat with a clean, stainless steel trowel.
2. Apply and level Senergy Finish during the same operation to minimum obtainable thickness consistent with uniform coverage.
3. Maintain a wet edge on Senergy Finish by applying and texturing continually over the wall surface.
4. Work Senergy finish to corners, joints or other natural breaks and do not allow material to set up within an uninterrupted wall area.
5. Float Senergy Finish to achieve final texture.

K. BASF Specialty Finish:

1. BASF AURORA TC-100 Finish:
 - a. Apply BASF TINTED PRIMER to substrate in accordance with current BASF TINTED PRIMER product bulletin.
 - b. BASF TINTED PRIMER shall be of corresponding color for selected BASF AURORA TC-100 Finish color. Allow BASF TINTED PRIMER to dry to the touch before proceeding to BASF AURORA TC-100 Finish application.
 - c. Apply a tight coat of finish with a clean, stainless steel trowel.
 - d. Maintain a wet edge on finish by applying and leveling continually over the wall surface.
 - e. Work finish to corners, joints or other natural breaks and do not allow material to set up within an uninterrupted wall area. Allow first coat to set until surface is completely dry prior to applying a second coat of finish.
 - f. For a smooth appearance, use a stainless steel trowel and apply the second coat of finish. Achieve final texture using circular motions.
 - g. For a textured appearance, apply the second coat of finish using a spray gun and hopper. Double-back to achieve final texture.
 - h. Total thickness of finish shall be approximately 1/16" (1.6 mm).
2. BASF AURORA STONE Finish:
 - a. Apply BASF TINTED PRIMER to substrate in accordance with current BASF TINTED PRIMER product bulletin.
 - b. BASF TINTED PRIMER shall be of corresponding color for selected BASF AURORA STONE Finish color. Allow BASF TINTED PRIMER to dry to the touch before proceeding to BASF AURORA STONE Finish application.
 - c. Apply a coat of BASF AURORA STONE Finish using a spray gun and hopper, maintaining a wet edge. Work to corners, joints or other natural breaks and do not allow material to set up within an uninterrupted wall area.
 - d. Allow first coat of BASF AURORA STONE Finish to set until surface is completely dry prior to applying a second coat of BASF AURORA STONE Finish.
 - e. Apply a second coat of BASF AURORA STONE Finish using a spray gun and hopper; double back to achieve final texture.
 - f. Thickness of BASF AURORA STONE Finish may vary between 1/16" (1.6 mm) 1/8" (and 3.2 mm), depending upon texture.

Note: Spraying of BASF AURORA STONE shall be in the same manner and direction and by the same mechanic on a particular elevation or project whenever possible, to maintain a uniform appearance. Maintain consistent air pressure to minimize texture variations. Stator or rotor design pumps are not recommended.

3. BASF ALUMINA Finish:
 - a. Apply BASF TINTED PRIMER to substrate in accordance with current BASF TINTED PRIMER product bulletin.
 - b. BASF TINTED PRIMER shall be of corresponding color for selected BASF ALUMINA Finish color. Allow BASF TINTED PRIMER to dry to the touch before proceeding to BASF ALUMINA Finish application.
 - c. Apply a tight coat of finish with a clean, stainless steel trowel.
 - d. Maintain a wet edge on finish by applying and leveling continually over the wall surface.
 - e. Work finish to corners, joints or other natural breaks and do not allow material to set up within an

- f. uninterrupted wall area. Allow first coat to set until surface is completely dry prior to applying a second coat of finish.
- g. Use a stainless steel trowel and apply the second coat of finish. Achieve final texture using circular motions
- h. Total thickness of finish may be between 1/16" (1.6 mm) and 1/8" (3.2 mm).

L. BASF Glaze/Stain:

1. BASF ANTICOGLAZE:

- a. Apply BASF ANTICOGLAZE in accordance with recommendations contained in current product literature.

3.05 CLEANING

- A.** Clean work under provisions of Section [01 74 00] [].
- B.** Clean adjacent surfaces and remove excess material, droppings, and debris.

3.06 PROTECTION

- A.** Protect base coat from rain, snow and frost for 48–72 hours following application.
- B.** Protect installed construction under provisions of Section [01 76 00] [].

END OF SECTION

WARRANTY

BASF warrants this product to be free from manufacturing defects and to meet the technical properties on the current Product Bulletin, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. **BASF MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS.** The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is shipment to purchaser of product equal to the amount of product that fails to meet this warranty or refund of the original purchase price of product that fails to meet this warranty, at the sole option of BASF. In the absence of an extended warranty issued by BASF, any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. **BASF WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.**

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on BASF's present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. BASF reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.