

# MasterSeal<sup>®</sup> 620

A bitumen / rubber latex emulsion. Surface applied, flexible, damp and vapour-proof liquid membrane

## DESCRIPTION

**MasterSeal 620** is a brown rubber/bitumen liquid emulsion with excellent adhesion which dries to a tough black seamless, flexible damp-proof and vapour-proof membrane.

## PRIMARY USES

- Damp-proofing structures: to provide an impervious damp-proof membrane on concrete and brick.
- Floors: to provide a sandwich membrane in new construction or a surface treatment.
- Walls: for interior and exterior walls.
- Roofs: for the maintenance of many types of roofs including built-up felt, asphalt, lead, zinc, aluminium, concrete, lightweight screeds, timber, slate, asbestos cement, corrugated iron, and as a vapour barrier.
- As an adhesive: for bonding wood blocks and wood mosaics, insulation board, expanded polystyrene and cork tiles and to provide a key for plastering.

## COMPOSITION

**MasterSeal 620** is a thixotropic cold applied bitumen emulsion with added rubber latex.

## PACKAGING

**MasterSeal 620** is supplied in 200 litre containers.

## TYPICAL PROPERTIES\*

Colour	Dark brown
Density	approx. 1kg/litre @ 25°C
Flashpoint	Non flammable
Service temperature	-30°C to +100°C
Application temperature	+5°C to 55°C
Rubber content	10% in the dried film
VOC	Nil

## STANDARDS

Fire Classification - BS EN ISO 11925 Part 2 / BS EN 13501 Part 1:2007 + A1:2009

## APPLICATION PROCEDURE

**MasterSeal 620** may be applied by brush or squeegee. All surfaces to which **MasterSeal 620** is applied must be sound, stable with an even finish and free from dirt, dust, loose debris, grease etc. It may be applied to damp but not waterlogged surfaces. Hot, very dry or porous surfaces should be dampened with a priming coat before **MasterSeal 620** is applied. Where subsequent coats are to be applied, the first coat must be dry.

### BELOW GROUND PROTECTION

**MasterSeal 620** may be applied to green concrete immediately after shuttering has been removed. Blind the first coat with clean sharp sand to afford higher dry film thickness and aid monitoring layer applications.

### SANDWICH MEMBRANE

Two coats to be applied at right angles, blind second coat with clean sharp sand to provide a mechanical key for top screed (minimum thickness 50mm). **MasterSeal 620** membrane should marry up with D.P.C. (where applicable).

### WALLS WITH DAMPNES

Remove any coatings and plaster back to the blockwork. Apply three coats of **MasterSeal 620** blinding the final layer with clean sharp sand whilst still tacky. Replaster using a render modified with **MasterCast 141**.

### CURING / DRYING

- MasterSeal 620** will take longer to dry sufficiently for over-coating in low temperatures and high humidity.
- Provisions of good ventilation will significantly reduce drying time.
- MasterSeal 620** should allowed to dry for 3-5 days.

### EQUIPMENT CARE

Before **MasterSeal 620** has dried, clean tools using soapy water. If dried, remove by scraping and with paraffin or white spirit.

# MasterSeal<sup>®</sup> 620

**A bitumen / rubber latex emulsion. Surface applied, flexible, damp and vapour-proof liquid membrane**

## SPECIFICATION CLAUSE

All areas indicated shall receive 2 or 3 coats as recommended of a high build rubber/ bitumen emulsion such as **MasterSeal 620** as manufactured by BASF, or similar approved.

## COVERAGE

Use	Number of coats	m <sup>2</sup> / litre		
		1st coat	2nd coat	3rd coat
Priming coat: (when required) Diluted with five parts water	1	7.50		
Damp-proofing and protective coating of structures: Bridge abutments, retaining walls, culverts, concrete or brick foundations, concrete columns and beams.	2	2	2.25	
Floors: sandwich membrane surface treatment	2 2	1.50 2.00	1.50 2.00	
Walls: interior and exterior	3	2.25	2.25	2.25
Roofs (with reinforcing scrim) felt, asphalt, lead, zinc, aluminium, concrete, timber, slate or corrugated roofs. Vapour barrier.	3 2	1 1	1.50 1.50	1.50
Adhesive: wood blocks, wood mosaics insulation board, expanded polystyrene, cork slabs. Plastering on difficult surfaces.	1 2	1.50 4.50		4.50

## SAFETY PRECAUTIONS

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs. Treat splashes to eyes and skin immediately. If

accidentally ingested, seek immediate medical attention. Reseal containers after use.

## STORAGE

Store under cover out of direct sunlight and protect from extremes of temperature. In tropical climates the product must be stored in an air conditioned environment. As with all bitumen emulsions, some settlement will occur with prolonged storage. It is, therefore, necessary to invert drums every other week to disperse the settlement. Shelf life is up to 1 year, in unopened containers, when stored as above. Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult BASF's Technical Services Department.

## NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF representative. BASF reserves the right to have the true cause of any difficulty determined by accepted test methods.

## QUALITY AND CARE

All products originating from BASF's Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and OHSAS 18001.

\* Properties listed are based on laboratory controlled tests.

# MasterSeal<sup>®</sup> 620

A bitumen / rubber latex emulsion. Surface applied, flexible, damp and vapour-proof liquid membrane

MBS\_CC-UAE/SI\_620\_04\_95/v4/05\_16

© = nhãn hiệu đã đăng ký của thành viên MBCC Group ở nhiều quốc gia

<b>TRÁCH NHIỆM</b>	Các thông tin kỹ thuật và hướng dẫn thi công trong các tài liệu của Hóa Chất Xây Dựng MASTER BUILDERS SOLUTIONS dựa trên cơ sở khoa học và kinh nghiệm thực tế. Do các thông tin ở đây chỉ nêu lên bản chất chung, không có giả thiết nào chung cho việc sử dụng và thi công riêng biệt của bất kỳ sản phẩm nào, nên người sử dụng cần phải kiểm tra mức độ thích hợp của sản phẩm theo từng trường hợp.
<b>CHÚ Ý</b>	Hóa Chất Xây Dựng MASTER BUILDERS SOLUTIONS cung cấp sản phẩm và hướng dẫn kỹ thuật nhưng không bao gồm trách nhiệm giám sát. Nên sử dụng sản phẩm theo sự chỉ dẫn của Hóa Chất Xây Dựng MASTER BUILDERS SOLUTIONS, tuy nhiên phải tuân thủ theo sự thay đổi, điều chỉnh của các chủ đầu tư, kỹ sư hoặc nhà thầu trong việc thi công vào từng môi trường ứng dụng thích hợp.

## Công Ty TNHH Master Builders Solutions

Trụ sở chính: Lầu 11, Saigon Trade Center, 37 Tôn Đức Thắng, P. Bến Nghé, Quận 1, Tp. Hồ Chí Minh, Việt Nam

Điện thoại: +84 329 702 998

Mã số thuế: 0316341574

Website: <https://www.master-builders-solutions.com/vi-vn>