

## MasterBrace® ADH 2200

### A high strength, non-flow epoxy bedding and repair mortar

THIS METHOD STATEMENT COVERS THE SEALING OF NON-STRUCTURAL STATIC CRACKS IN CONCRETE THAT DO NOT EXTEND TO THE REINFORCING STEEL.

A SMOOTH EPOXY PASTE SUITABLE FOR SEALING SURFACE CRACKS BLOW HOLES AND OTHER SURFACE DEFECTS IN CONCRETE.

#### METHOD STATEMENT: MasterBrace ADH 2200 (7.5kg kit)

#### 1. GENERAL:

- 1.1. Chase the crack using a chisel to V the crack at the surface or use an angle grinder to open up the crack.
- 1.2. Wire brush, then blow dust and debris from the crack.

#### 2. MIXING:

- 2.1. The mixing of a full kit of **MasterBrace ADH 2200** (7.5kg) If required to mix a full 7.5kg kit at one time, this should be done using a spiral mixer and heavy-duty drill.
- 2.2. Mix components A and B together until a uniform streak free colour is obtained. In cold weather if the mixed material is too stiff to apply, mix the material using rubber gloved hands that have been dipped in water. The inclusion of the moisture will make the material smoother. Alternatively, pre-heat the two components (in their containers) in warm water.
- 2.3. Partial mixing of **MasterBrace ADH 2200** tends to be the norm and should be carried out using the 60/40 ratio of Part A to Part B by volume and mixing should be done on a non-absorbent surface using a suitable flexible steel scrapper / trowel until a smooth streak-free colour is obtained.

### 3. APPLICATION:

- 3.1. Using a spatula, apply the **MasterBrace ADH 2200** into the routed-out crack, forcing the material into the concrete surface.
- 3.2. Smooth off the surface with the spatula.
- 3.3. To fill blow holes etc. in concrete prior to overcoating, tight trowel the **MasterBrace ADH 2200** into the prepared surface.

#### 4. TEMPERATURE CONDITIONS:

- 4.1. This repair system shall be used when the surface and ambient temperature is above 10°C and will remain so during the curing period.
- 4.2. In hot weather areas to be repaired shall be shaded from direct sunlight.

#### 5. CURING:

5.1. No curing is required.

MBCC GROUP



# MasterBrace® ADH 2200

### A high strength, non-flow epoxy bedding and repair mortar

® = registered trademark of a MBCC Group member in many countries of the world

STAT	EMEN	TOF
SIAI	CIAIL	1 01
DECD	ONCH	BILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by Master Builders Solutions either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Master Builders Solutions, are responsible for carrying out procedures appropriate to a specific application.

#### Master Builders Solutions Ltd.,Co.

Level 11, Saigon Trade Center, 37 Ton Duc Thang, Ben Nghe Ward, District 1, Ho Chi Minh City, Vietnam

Tel: +84 329 702 998

Register number: 0316341574

Website: https://www.master-builders-solutions.com/vi-vn