

# MasterTop<sup>®</sup> P 1602

## Solvent free primer for MasterTop and MasterSeal systems

### DESCRIPTION

MasterTop P 1602 is a solvent free, low viscosity, two component epoxy resin based primer for BASF polymer flooring and waterproofing systems.

### RECOMMENDED USES

MasterTop P 1602 is designed for use as a primer on substrates such as concrete and cementitious screed to install MasterTop floor coating systems and MasterSeal waterproofing membranes.

### FEATURES AND BENEFITS

- Solvent-free—Avoids bubbles and blisters in the topping
- Low viscosity—Effective sealing of pores; enhances topping finish
- High bond strength— Enables the topping to behave monolithic with substrate
- Pre-proportioned packing —Eliminates batching errors

### PROPERTIES

Mixed density @ 20°C	1.62 g/cm <sup>3</sup>
Mixing ratio (by weight)	100:22
Bond strength (tensile) N/mm <sup>2</sup>	>2 (concrete failure)
Viscosity (mixed) @ 250C	1000mPas
Pot Life @10°C	60 Minutes
@23°C	35 minutes
@30°C	20 minutes
Overlay time	1 day to 2 days

### APPLICATION

#### (A) SURFACE PREPARATION

Remove all grease, oil, dust, residual curing compound, mould release agent or other contaminant that could impair adhesion. Conventional concrete curing compounds should be removed before application. Laitance should preferably be removed by light sweep blasting or hydro-jetting. Mechanical wire brushing may be appropriate for small areas. Spalled concrete should be cut back to sound concrete and made good with a suitable cementitious MasterEmaco<sup>®</sup> repair mortar or a scratch coat of MasterTop P 1602.

The compressive strength of the substrate shall not be less than 25 N/mm<sup>2</sup>. The concrete slab in contact with the ground must have a vapour barrier installed in compliance with DIN 18195 or equivalent. After pre-treatment of the substrate, the bond strength of the substrate must be at least 1.5 N/mm<sup>2</sup>.

The moisture content of the substrate shall not be higher than 4% throughout. The temperature of the substrate must be at least 3°C above the current dew point temperature.

Protect walls and columns against resin splashes using masking tape and plastic sheeting.

#### (B) MIXING

Before mixing, precondition both A and B components to a temperature of approximately 15 to 25°C. Mix mechanically using a slow speed (300 rpm) drill with a wing type mixing paddle. Mix Part A slowly in its container, then add all of Part B container to it while continuing to mix for 2 to 3 minutes.

#### (C) PLACING

Do not apply at substrate temperatures below 5°C. Apply MasterTop P 1602 immediately after mixing, spread to the floor as soon as possible and complete the application within 30 minutes after mixing.

Apply the coating by brush or roller working the primer into the pores of the substrate to ensure that the surface is sealed. To achieve complete sealing of porous substrates, two coats will be required; the second coat applied 24 hours later and at right angles to the first.

If the surface has been treated with fairing coat as described under surface preparation, allow the fairing coat to set and within 24 hours apply the first coat of MasterTop P 1602. If used as primer for MasterSeal membranes always lightly sand seed whilst the material is still tacky.

#### (D) CURING

MasterTop P 1602 is self-curing. During the curing process, protect the primer from direct contact with water for approx. 24h.

#### (E) SUBSEQUENT COATS

Install the desired polymer top coat 24 hours after the application of primer.

# MasterTop<sup>®</sup> P 1602

Solvent free primer for MasterTop and MasterSeal systems

## ESTIMATING DATA

Consumption of the mixed Mastertop P 1602 is dependent on the surface porosity and roughness. On average quality substrate, typical consumption will be 300 to 600g/m<sup>2</sup>. So each package is roughly for 40m<sup>2</sup>.

## PACKAGING

Mastertop P 1602part A: 10kg Container  
Mastertop P 1602part B: 2.2kg Container

## SHELF LIFE

Mastertop P 1602can be stored for 18 months from the date of manufacture if stored in original unopened packing, in a dry enclosed space at 15 and 35°C.

## PRECAUTIONS

For the full health and safety hazard information and how to safely handle and use this product, please make sure that you obtain a copy of the BASF Material Safety Data Sheet (MSDS) from our office or our website.

ID# MasterTop P1601CHI v1.1 0113

® = registered trademark of a MBCC Group member in many countries of the world

---

### STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

---

### NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by Master Builders Solutions either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Master Builders Solutions, are responsible for carrying out procedures appropriate to a specific application.

---

### Master Builders Solutions Ltd.,Co.

Level 11, Saigon Trade Center, 37 Ton Duc Thang, Ben Nghe Ward, District 1, Ho Chi Minh City, Vietnam  
Tel: +84 329 702 998  
Register number: 0316341574  
Website: <https://www.master-builders-solutions.com/vi-vn>