

MasterGlenium 118

Polycarboxylic ether-based superplasticizer to produce high-quality ready-mix concrete

MATERIAL DESCRIPTION

MasterGlenium 118 is an innovative latest generation superplasticizer based on polycarboxylic ether (PCE) polymers and is specially engineered for ready-mix concrete.

MasterGlenium 118 greatly improves cement dispersion. At the start of the mixing process the same electrostatic dispersion occurs but the presence of the lateral chains, linked to the polymer backbone, generate a steric hindrance which stabilises the cement particles capacity to separate and disperse. This mechanism provides flowable concrete with greatly reduced water demand.

FIELD OF APPLICATION

MasterGlenium 118 is used to produce high-quality ready-mix concrete.

FEATURES AND BENEFITS

- Capability of delivering high performance concrete.
- Production of a concrete with low water cement ratios with excellent workability retention properties.
- A versatile product for many application requirements.
- Easier placing and faster strength development.
- Improved concrete surfaces.
- Insurance that concrete meets original specification.
- High quality durable concrete.

TYPICAL PROPERTIES*

Properties listed are for guidance and are not a guarantee of performance.

Appearance	Brownish liquid
Specific gravity @25°C	1.060 -1.080
pH value	5.0 – 7.0
Chloride Content	"Chloride-free" to EN 934-2

The occurrence of a surface layer with **MasterGlenium 118** is normal and will have no effect on the performance of the product.

CLASSIFICATION AND STANDARDS

ASTM C-494 Type F&G
 BS EN 934-2

DOSAGE

The normally recommended dosage rate of **MasterGlenium 118** is 0.4 to 1.5 litres per 100kg of total cementitious material. Other dosages may be recommended in special cases according to specific site conditions. In this case, please consult our Technical Services Department for advice.

It is recommended that trials be conducted with the actual materials to be used and at the specified **MasterGlenium 118** dose rates to verify performance before proceeding to application.

MIXING

MasterGlenium 118 is a ready-to-use admixture to be added to the concrete as a separate component. Optimal results are obtained if **MasterGlenium 118** is poured into the concrete mix right after the addition of the first 80% of the mixing water, i.e. when all solids are wetted. Avoid adding the admixture to the dry aggregates.

MasterGlenium 118

Polycarboxylic ether-based superplasticizer to produce high-quality ready-mix concrete

COMPATIBILITY

MasterGlenium 118 is not compatible with MasterRheobuild superplasticizers.

MasterGlenium 118 is suitable for mixes containing:

- Microsilica (Silica Fume)
- Fly Ash (PFA)
- GGBS (ground granulated blast furnace slag)

PACKAGING

MasterGlenium 118 is available in 20L, 1000 litre IBCs or in bulk.

STORAGE / SHELF LIFE

MasterGlenium 118 should be stored out of direct sunlight and protected from extremes of temperatures. The shelf life is 12 months from date of manufacture when stored as above.

SAFETY PRECAUTIONS

MasterGlenium 118 contains no hazardous substances requiring labelling. For further information refer to the Material Safety Data Sheet.

NOTE

Technical support, where provided, does not constitute supervisory responsibility. For additional information contact your local MB Construction Chemicals Solutions South Africa (Pty) Ltd representative. MB Construction Chemicals Solutions South Africa (Pty) Ltd shall not be liable for technical advice provided.

MB Construction Chemicals Solutions South Africa (Pty) Ltd reserves the right to have the true cause of any difficulty determined by accepted test methods. Undertaking such tests is not, and shall not be deemed to be, an admission of liability or an assumption of any risk, loss, damage or liability.

QUALITY AND RESPONSIBLE CARE

All products originating from MB Construction Chemicals Solutions South Africa (Pty) Ltd are manufactured under a management system independently certified to conform to the requirements of the quality standards ISO 9001, environmental and occupational health and safety standards.

* Properties listed are based on laboratory controlled tests.

DISCLAIMER

The technical information and application advice given in this MB Construction Chemicals Solutions South Africa (Pty) Ltd publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.