

MasterRoc MG 01

High yield thixotropic cable bolt grout

MATERIAL DESCRIPTION

MasterRoc MG 01 is a high yield, shrinkage compensated and thixotropic grout for placement of cable and rock bolts in civil tunnels and underground mines.

RECOMMENDED USES

MasterRoc MG 01 is particularly suitable as a grout used for the encapsulation of roof bolts and cable anchors where the “top-down” grouting method is preferred.

MasterRoc MG 01 has been specially developed to give a high yield (volume) of grout without segregation or bleed whilst providing excellent compressive strengths.

FEATURES AND BENEFITS

- Extremely pumpable but shows rapid thixotropy to restrict flow into surrounding strata.
- Economical to use, due to high yield and rapid thixotropy.
- Small grout tube diameters mean smaller diameter drill holes can be used.
- Eliminates the requirement for sealing of the collar and plate with cotton waste etc.
- Good ultimate strength to ensure the permanence and safety of critical installations.
- Extended working time (over 30 minutes at 20°C) enabling easier cleanup of pumps and hoses.
- Shrinkage compensated for greater bond strength to surrounding strata.
- High bond to steel.

PERFORMANCE DATA

Grout strength development is dependent on the amount of mixing water, ambient temperature, age, and curing. Typical rates of compressive strength development for 20kg of **MasterRoc MG 01** grout with 6.5l of water under controlled laboratory conditions are shown below:

Compressive Strength – Typical results (AS1478.2 Appendix A. restrained 50mm cubes at 23°C

1 Day	7 Days	28 Days
30 MPa	65 MPa	80 MPa

MIXING EQUIPMENT

For best results mix using a high mechanical shear or paddle mixer. Any grout pump must have accurate water dosage facilities.

MIXING

MasterRoc MG 01 is supplied ready to use, requiring only the addition of potable water. Do not use hardened or lumpy grout caused by torn or water damaged bags.

Fill mixer with correct volume of water to match number of bags of **MasterRoc MG 01**. A good mixer should have an accurate method of determining the water content.

Start the mixer and slowly add **MasterRoc MG 01** powder. Continue mixing the grout until a thick creamy, no-lump consistency is obtained.

Actual amount of water will depend on the desired consistency of the grout required and the grout pump available. As a guide, use 6.5-7.5 litres per 20kg bag.

Do not use excess water (above 7.5 litres for thixotropic mixes). Discard any grout that has been left in excess of 60 minutes. Do not retemper.

PLACEMENT

Master Builders Solutions provide a range of support services which includes operator training and underground audits. Each service package is developed to suit individual site requirements.

It is strongly recommended that a review with fully trained and qualified Master Builders Solutions personnel is conducted prior to placement of **MasterRoc MG 01**.

CLEANING

As with all grouting operations, systematic cleaning of the pump and grout lines with clean water is essential. This should be done immediately after completion of grouting operations. If delays occur for greater than 1 hour, the batched grout should be discarded, and the pump and grout lines cleaned.

MasterRoc MG 01

High yield thixotropic cable bolt grout

ESTIMATING DATA

20kg of **MasterRoc MG 01** grout with 7.5 litres of water will yield approximately 14.5 litres (0.0145m³).

PACKAGING

MasterRoc MG 01 is packaged in 20kg moisture resistant paper bags and supplied 64 bags (1.28t) to a pallet.

STORAGE AND SHELF LIFE

Pallets should be stored in a dry place. **MasterRoc MG 01** has a shelf life of 12 months.

PRECAUTIONS

For the full health and safety hazard information and how to safely handle and use this product, make sure that you obtain a copy of the Master Builders Solutions Safety Data Sheet (SDS).

NOTE

Technical support, where provided, does not constitute supervisory responsibility. For additional information contact your local MB Construction Chemicals Solutions South Africa (Pty) Ltd representative. MB Construction Chemicals Solutions South Africa (Pty) Ltd shall not be liable for technical advice provided.

MB Construction Chemicals Solutions South Africa (Pty) Ltd reserves the right to have the true cause of any difficulty determined by accepted test methods. Undertaking such tests is not, and shall not be deemed to be, an admission of liability or an assumption of any risk, loss, damage or liability.

QUALITY AND RESPONSIBLE CARE

All products originating from MB Construction Chemicals Solutions South Africa (Pty) Ltd are manufactured under a management system independently certified to conform to the requirements of the quality standards ISO 9001, environmental and occupational health and safety standards.

* Properties listed are based on laboratory controlled tests.

DISCLAIMER

The technical information and application advice given in this MB Construction Chemicals Solutions South Africa (Pty) Ltd publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.