

MasterSeal P 101

Universal modified silane primer for use with MasterSeal 470 and SONOLASTIC series sealants

MATERIAL DESCRIPTION

A liquid primer used in the preparation of joint surfaces prior to the use of **MasterSeal 470** sealants.

MasterSeal P 101 is used when preparing porous surfaces such as concrete, brickwork, stonework, asbestos and timber and non-porous surfaces such as stainless steel and ceramics.

PACKAGING

MasterSeal P 101 is available in 750ml tins.

APPLICATION TEMPERATURE

5°C to 40°C.

COVERAGE

Theoretical coverage approx. 20m² per litre.

WATCHPOINT

Due to the penetrating and sealing action of **MasterSeal P 101**, staining may occur on materials such as granite, marble, natural stone and man-made composites. If in doubt consult Master Builders Solutions' Technical Services Department.

DIRECTIONS FOR USE

Preparation of surfaces:

Joint faces to be primed must be completely dry and free from all dirt, dust, cement laitance and other loose and deleterious matter. This is best achieved by grit or sand blasting or thorough wire brushing and then blowing clean with oil free compressed air.

Storage:

Pour a small amount of the primer into a clean container ensuring that the main container is tightly resealed. Liberally apply a coat of primer with a soft brush to the required surface. Allow to become tack free before installing MasterSeal sealants.

If primer is left for more than 3 hours re-priming is necessary.

Note: MasterSeal primers are solvent based.

EQUIPMENT CARE

Clean all brushes immediately with **MasterTop THN 2**.

SAFETY PRECAUTIONS

Flammable or highly flammable liquids. Do not apply when smoking or near naked flame. Wear protective gloves and goggles. Use in well ventilated areas and avoid breathing of vapour.

In the event of narcosis by inhalation of concentrated vapour, remove person to fresh air and call for medical attention. If in contact with eyes, irrigate thoroughly for at least five minutes with clean, cold water and seek medical attention.

In the event of a fire, extinguish with carbon dioxide, dry chemical or foam fire extinguisher.

STORAGE

Store under cover out of direct sunlight and protect from extremes of temperature. In tropical climates the product must be stored in an air-conditioned environment. Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult Master Builders Solutions' Technical Services Department.

MasterSeal P 101

Universal modified silane primer for use with MasterSeal 470 and SONOLASTIC series sealants

NOTE

Technical support, where provided, does not constitute supervisory responsibility. For additional information contact your local MB Construction Chemicals Solutions South Africa (Pty) Ltd representative. MB Construction Chemicals Solutions South Africa (Pty) Ltd shall not be liable for technical advice provided.

MB Construction Chemicals Solutions South Africa (Pty) Ltd reserves the right to have the true cause of any difficulty determined by accepted test methods. Undertaking such tests is not, and shall not be deemed to be, an admission of liability or an assumption of any risk, loss, damage or liability.

QUALITY AND RESPONSIBLE CARE

All products originating from MB Construction Chemicals Solutions South Africa (Pty) Ltd are manufactured under a management system independently certified to conform to the requirements of the quality standards ISO 9001, environmental and occupational health and safety standards.

* Properties listed are based on laboratory controlled tests.

DISCLAIMER

The technical information and application advice given in this MB Construction Chemicals Solutions South Africa (Pty) Ltd publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.