

MasterSeal P 684

One-component polyurethane primer for non-ferrous metals and stainless steel of the MasterSeal Roof 2111 and MasterSeal Roof 2160 systems.

MATERIAL DESCRIPTION

MasterSeal P 684 is a one-component, polyurethane, moisture-curing, fast-curing, solvent-based primer.

FIELDS OF APPLICATION

The product is suitable as a primer in MasterSeal Roof systems if the substrate consists of stainless steel, non-ferrous metals and in particular on aluminum and zinc.

FEATURES AND BENEFITS

For the technical characteristics, refer to the performance of the entire MasterSeal Roof 2160 and MasterSeal Roof 2111 system.

In compliance with the European Regulation (EU No 305/2011 and EU No. 574/2014) the product is provided with the CE marking according to UNI EN 1504-2 and UNI EN 13813 4891 and the relative DoP (Declaration of Performance).

THEORETICAL CONSUMPTION

0.03 - 0.06 kg / m².

These consumptions are to be considered purely indicative and may increase in the case of very rough substrates.

PACKAGES

4.7 kg can

STORAGE

Store the material in the original containers, in a dry and covered place at a temperature between 15 and 25°C. Do not expose to direct sunlight.

Technical data	
Packaging	4.7 kg can
Consumption	0.03 - 0.06 kg / m ²
Density of the mixture	0.9 kg / liter
Solid residue	25%
Recoating times	10°C: 2 - 4 hours 20°C: 30 min - 2 hours 30°C: 15 min - 1 hour
Relative humidity tolerated	90%

APPLICATION SHEET

For any details on correct application, always refer to the specific application guide "MasterSeal Roof Systems: Roof Waterproofing Application Manual" and any other specific manuals for which it is intended to be used. For more information, contact the Technical Service.

TEMPERATURE

The application can take place when the ambient temperature is between + 5°C and + 40°C.

MIXING

Before applying, bring the material to a temperature of approximately 15 to 25°C. MasterSeal P 684 contains pigments that could deposit on the bottom, so it is good practice to shake the container well before use.

APPLICATION

The best way to apply it is with a brush or cloth. Spread it everywhere creating a thin layer, being careful not to apply excess.

TOOL CLEANING

Clean tools immediately after use with a diluent. Hardened material on tools and mixer can be removed mechanically

WARNINGS

MasterSeal are products for professional use. For further information, consult the Master Builders Solutions Italia Spa area technician.

SAFETY INSTRUCTION

For information on the correct and safe use, transport, storage and disposal of the product, consult the most recent Safety Data Sheet.

MasterSeal P 684

One-component polyurethane primer for non-ferrous metals and stainless steel of the MasterSeal Roof 2111 and MasterSeal Roof 2160 systems.

OTHER SERVICES

For price analysis, specifications, supplementary brochures, references, reports and technical assistance, visit the website www.master-builders-solutions.com/it-it or contact infomac@mbcc-group.com.



Scan the QR code to visit the product page and download the latest version of this datasheet.

Since 16/12/1992, Master Builders Solutions Italia Spa has been operating under a Certified Quality System compliant with the UNI EN ISO 9001 Standard. Furthermore, the Environmental Management System is certified according to the UNI EN ISO 14001 Standard and the Safety Management System is certified according to the UNI ISO 45001 Standard.

Master Builders Solutions Italia Spa

Via Vicinale delle Corti, 21 – 31100 Treviso – Italia
T +39 0422 429200 F +39 0422 421802
www.master-builders-solutions.com/it-it
e-mail: infomac@mbcc-group.com

For further information, please consult the local Technician of Master Builders Solutions. The technical advice on how to use our products, either written or verbally given, are based on the current state of our scientific and practical expertise, and does not imply the assumption of any guarantee and/or responsibility for the final results of works executed using our products.

Therefore, the customer is not exempted from the exclusive task and responsibility of verifying the suitability of our products for the intended use and purposes.

This version supersedes all the previous ones.